

REVIEW

Intraoral repair of fractured ceramics: a literature review

[version 1; peer review: 2 approved, 2 approved with reservations]

Firas K. Alqarawi¹, Abdulkareem A. Alhumaidan², Abdulrahman Aldakhili¹, Abdullah Alfayez¹, Tahani Abushowmi¹, Anwar Alramadan¹, Fawaz Alzoubi¹

¹Department of Substitutive Dental Sciences, College of Dentistry, Imam Abdulrahman Bin Faisal University, Dammam, Eastern Region, 31441/P.O. Box 1982, Saudi Arabia

²Department of Preventive Dental Sciences, College of Dentistry, Imam Abdulrahman Bin Faisal University, Dammam, Eastern Region, 31441/P.O. Box 1982, Saudi Arabia

³Department of General Dental Practice, Faculty of Dentistry, Kuwait University, Safat, 13110/P.O. Box 24923, Kuwait

 First published: 08 Nov 2022, 11:1275 https://doi.org/10.12688/f1000research.126547.1
 Latest published: 08 Nov 2022, 11:1275 https://doi.org/10.12688/f1000research.126547.1

Abstract

Background: Fracture or chipping of veneering ceramic resulting in aesthetic and functional issues is a frequent technical complication encountered with fixed dental prostheses. Treatment options include extraoral or intraoral repair of the ceramic restoration; the latter being minimally invasive and cost-effective. We reviewed the various intraoral repair techniques for ceramic fractures and their efficiency in the last decade.

Methods: A literature search was carried out between 2017 and 2022 using the PubMed database with keywords: intraoral, repair, ceramics, porcelain, and 'porcelain fused to metal'. Screening of abstracts and full texts was carried out to determine the final list of eligible studies. **Results:** Twenty-one eligible studies were included in the review which consisted of 17 in vitro studies, three case reports, and one prospective clinical study. Researchers and dentists preferred repairing cracked veneered zirconia-based restorations intraorally if the restoration is in acceptable condition. However, successful intraoral repair of veneering fractures relies on the bond between the previous restoration and the new repair material, the right adhesive resin, and adequate surface conditioning. The review indicated that the best technique to fix chipping in a complex made of zirconia core and veneering ceramic is to treat the veneering ceramic with hydrofluoric acid before covering the core ceramic with silica. **Conclusion:** Intraoral repair is an efficient and economic procedure without the need for repeated sessions. However, the success and longevity of the restoration rely on the technical skills of the clinicians and adherence to prescribed protocols.

Keywords

Intraoral, restoration, ceramics, fixed partial dentures, zirconia, porcelain chipping, veneering.

Open Peer Review



- 1. **Lomaya Ghanem**, Misr International University, Cairo, Egypt
- 2. **Philipp-Cornelius Pott** D, Hannover Medical School, Hannover, Germany
- Rafael Delgado-Ruiz, State University of New York at Stony Brook, Stony Brook, USA Stony Brook University, School of Dental Medicine, Stony Brook, USA
- 4. **Punit Fulzele** D, Datta Meghe Institute of Higher Education & Research, Wardha, India

Any reports and responses or comments on the article can be found at the end of the article.

Corresponding author: Firas K. Alqarawi (fkalqarawi@iau.edu.sa)

Author roles: Alqarawi FK: Conceptualization, Investigation, Methodology, Writing – Original Draft Preparation, Writing – Review & Editing; Alhumaidan AA: Methodology, Project Administration, Supervision, Visualization, Writing – Original Draft Preparation; Aldakhili A: Data Curation, Formal Analysis, Investigation, Methodology, Writing – Original Draft Preparation; Alfayez A: Data Curation, Formal Analysis, Investigation, Writing – Original Draft Preparation; Alfayez A: Data Curation, Formal Analysis, Investigation, Writing – Original Draft Preparation; Abushowmi T: Data Curation, Formal Analysis, Investigation, Writing – Original Draft Preparation; Alfayez A: Data Curation, Writing – Original Draft Preparation; Alzoubi F: Original Draft Preparation; Alzoubi F: Validation, Visualization, Writing – Review & Editing

Competing interests: No competing interests were disclosed.

Grant information: The author(s) declared that no grants were involved in supporting this work.

Copyright: © 2022 Alqarawi FK *et al.* This is an open access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

How to cite this article: Alqarawi FK, Alhumaidan AA, Aldakhili A *et al.* Intraoral repair of fractured ceramics: a literature review [version 1; peer review: 2 approved, 2 approved with reservations] F1000Research 2022, **11**:1275 https://doi.org/10.12688/f1000research.126547.1

First published: 08 Nov 2022, 11:1275 https://doi.org/10.12688/f1000research.126547.1

1. Introduction

Modern cosmetic dentistry places a strong emphasis on aesthetics, and thus finds a wide usage of ceramic and porcelain in teeth restoration to achieve the most natural-looking aesthetics. However, the accelerated usage of dental porcelains is accompanied by the risk of fractures (Hammond *et al.* 2009). Owing to its brittle nature, porcelain veneering, when exposed to masticatory forces, clenching, and moisture causes cracks or chipping (Rosentritt, Steiger *et al.* 2009). Studies have shown that the most frequent technical issue associated with dental restorations were ceramic fractures, which were followed by porcelain chipping and loss of retention (Vagropoulou, Klifopoulou *et al.* 2018). According to a systemic literature review, chipping of the veneering ceramic is one of the most frequent technical complications occurring at a rate of 12.7% following a three-year observation period (Pjetursson, Sailer *et al.* 2015). Consequently, patients with ceramic fractures might have aesthetic and functional issues that need an immediate fix. Direct repairs have been suggested in such conditions where the broken prosthesis displays good adaptation and acceptable aesthetics (Mesquita, Al-Haj Husain *et al.* 2021).

In bilayered dental prostheses, such as metal-ceramic fixed dental prostheses (FDP), fractures in veneering ceramic may be treated either by replacing the existing restoration or by repairing it intraorally. Removal of FDP can be challenging as it can lead to deformation of the metal and iatrogenic fracture of the sound tooth tissues that can seriously compromise the longevity of the tooth. Additionally, replacing FDPs is typically a difficult and expensive process that adds significantly to chairside time, which is not always well received by the patient (Özcan and Volpato 2017). Furthermore, it is associated with the risk of harming the tooth that serves as the abutment (Kocaağaoğlu, Manav *et al.* 2017).

On the other hand, intra-oral ceramic restoration repair is minimally invasive and most cost-effective making it an ideal choice (Aslam, Hassan *et al.* 2018). Furthermore, intraoral repair has recently been suggested as a potential therapy alternative if the indications and treatment techniques are suitable (Agingu, Zhang *et al.* 2018). Repairing the ceramic restoration intraorally is a temporary but effective solution. The easiest way is to polish the surface and prevent future failures. If the repair cannot be done by polishing, the missing part is replaced with composite resin, or the chipped part is cemented using resin cement. A new veneer layer is prepared and bonded to the existing restoration (Kimmich and Stappert 2013).

Intraoral repair is a simpler technique to treat veneer ceramic fractures than total replacement or extraoral repair methods (Polat, Tokar *et al.* 2021). Veneering porcelain flaws that expose the restoration's core material create a special challenge for intraoral repair. Particularly with metal frameworks, it can be challenging for the dentist to match the colour of the framework with veneer without compromising the aesthetic outcome. To achieve functional success, the dentist must effectively bond the veneering porcelain to the core material (Kimmich and Stappert 2013). However, selecting the best system that would deliver a trustworthy result is often difficult for clinicians. Hence, this article reviews studies that have investigated intraoral repair techniques for ceramic fractures and their efficiency in the last five years.

2. Methods

2.1 Data sources and search strategy

The literature search was conducted using the PubMed database for studies that investigated intraoral repair techniques for ceramic fractures. All studies published in English from January 2017 through August 2022 were considered for review. The search strategy was derived from appropriate keywords representing the concepts: "intraoral repair", "ceramics", "porcelain", "porcelain fused to metal", and "efficacy". The primary outcome of the review included the efficacy of the intraoral repair technique used. Articles were excluded if published in a language other than English, not published in the last five years, or if full text is unavailable.

After applying the criteria, study selection was undertaken by first screening the abstract and title followed by the full-text versions of relevant studies to determine the final list of eligible studies. Data were extracted from the studies following the completion of full-text screening. All data were summarized. No statistical analysis was performed.

3. Results

The literature search from PubMed retrieved 21 eligible studies that were included in this review to understand the intraoral repair techniques used for treating ceramic fractures. The findings of the included studies have been summarized in Table 1.

The current literature review included 17 *in vitro* studies, three case reports, and one prospective clinical study. Various ceramic types were included in these studies such as glass-based ceramics with three subclasses: predominantly glass (feldspathic glass), moderately filled glass (leucite), and highly filled glass (leucite disilicate based); glass-infiltrated ceramics (In-Ceram groups); and non-glass-based ceramics: polycrystalline ceramics (alumina, zirconia). Likewise,

	Conclusion	In comparison to HF plus Universal adhesive, ceramic surface treatment with HF plus silane plus traditional adhesive produced a greater SBS.	Intraoral repair of lithium disilicate glass ceramic when utilising GBL, should include the usage of rubber dam	Clinicians may favour Nd: YAG laser therapy or Nd: YAG laser therapy combined with HF to intraorally repair fractured areas	a. For each level of cracked zirconia ceramic, griding with a diamond bur improved the bond strength needed for repair	b. To get an appropriate binding strength between	framework, the manufacturer's instructions must be followed	When using a direct repair procedure, a problem resulting from a veneering ceramic's fracture or chipping can be resolved prompty and effectively without the need to			
	Age	ИА	NA	ИА	A						
	Number of participants/ samples	8	60	100	120				-		
	Study design	In vitro	In vitro	In vitro	In vitro		Case Report				
014110113.	Repair system	Composite resin	NR	R	Clearfil Repair and Clearfil Kajesty Esthetic				Clearfil Photoposterior		
נוווא וחו וומררמו במ רבו מוווור ו באת	Surface treatment	Laser and universal adhesive	1. Self-etching glass-ceramic primer (MEP) 2. Grit blasting	 Group H = HF etching Group N = Nd: YAG (neodymium: yttrium-aluminum-garnet) laser Group NH = Nd: YAG laser + HF gel Group E = Er: YAG (erbium: yttrium-aluminum-garnet) laser Group EH = Er: YAG laser + HF gel 	1. Control: Grinding	2. Sandblasting	3. Long pulse laser	4. Short pulse laser	Air abrasion, Etchant, Silane		
שוכעכ וושקשו ושוטא	Manufacturer	IPS Empress; IvoclarVivadent, Liechtenstein	Ivoclar Vivadent; Schaan, Liechtenstein	Celtra Duo, Dentsply De Trey, Bensheim, Germany	1. ICE Zirkon Translucent	2. Vita VMK Master	z. vra vmr Master		1. Lava	2. IPS e.max Ceram	
	Framework material/ Type of ceramic	Lucite- reinforced glass-ceramic plates	Lithium disilicate glass ceramic	Zirconia- Reinforced Lithium Silicate Ceramics	1. 100% Zirconia	2. 100% Veneering ceramic 3. 50% Veneering ceramic + 50% Zirconia		veneering ceramic + 50% Zirconia	1. Zirconia framework 2. Veneering ceramic		
	Author, year	Kiomarsi <i>et al.</i> , 2022	Höller <i>et al.</i> , 2022	Benli <i>et al.,</i> 2022	Polat <i>et al.</i> , 2021				Mesquita et al., 2021		
	SI. No.	~	2	m	4				Ю		

Table 1. Literature overview of intraoral repair systems for fractured ceramic restorations.

Table	1. Continued								
sı. No.	Author, year	Framework material/ Type of ceramic	Manufacturer	Surface treatment	Repair system	Study design	Number of participants/ samples	Age	Conclusion
9	Hakimaneh	Feldspathic	Kuraray	1. Etchant+Silane	Tetric N-Ceram	In vitro	60	NA	To strengthen the link
	et al., 2020	porcelain	Noritake Dental Inc	2. Silane+CO2 laser					between porcelain and composite resin,
				3. CO2 laser+Silane					Er: YAG irradiation
				4. Silane+Er: YAG laser					treatment is just as
				5. Er: YAG laser+Silane					advantageous as hydrofluoric (HF) acid
				6. Bur+Etchant+Silane					etching and silane treatment
2	Meirelles et al., 2020	Porcelain veneered zirconia FPD	VITA Zahnfabrik	Etchant and Silane	FILTEK Z350	Case Report	-	48 years	Intraoral repairs of chipped restoration were done in single sitting using
									composite resin that survived for more than 5 years
∞	Sanal and	Ceramic	VITA Zahnfabrik	Air abrasion	1. Vertise flow	In vitro	96	NA	Self-adhesive
	Kilinc, 2020	specimen (VITA VM 9; VITA VM 13;			2. Fusio Liquid Dentin				composites could be used instead of a repair kit with
		VITA VMK 95; and IPS e max			3. Constic				flowable composite for repairing chiming
		Ceram)			4. BISCO + Filtek Supreme				fractures of ceramics
σ	Gul and Altınok- Uygun, 2020	One feldspar ceramic and two resin nanoceramics	Vitablocks Mark II	1. Control Group	Composite resin	In vitro	96	AA	a. The ceramic type determines the success of CAD/CAM blocks
			Lava Ultimate	2. Acid Etching					b. Resin
			and Cerasmart	3. Cojet System					nanoceramics are more successful in
				4. Z-Prime Plus					intraoral repair applications
				5. GC Repair					-
				6. Cimara System					
				7. Porcelain Repair System					
				8. Clearfil repair system					

1						10	-		
	Conclusion	Universal adhesive systems make zirconia bonding easter and make intraoral repair of fracture possible	In comparison to the milling, the pressed fabrication method produced lithium disilicate restorations with much higher crown strength and fracture resistance	After 13 years of clinical monitoring, posterior FDP composed of veneered zirconia with either a fixed-to- fixed or a cantilever fixed or a cantilever design exhibit equivalent survival and success rates	a. Cohesive fractures are easier to repair than adhesive fractures	 b. The Clearfil repair material outperforms the P and R material utilized in this investigation for cohesive fractures 	c. For adhesive fractures, the material of choice is P and R repair material		
	Age	¥	МА	Mean age of women 55.7 years mean age of men 54.3 years	women 55.7 years mean age of men 54.3 years NA				
	Number of participants/ samples	S	60	8	06				
	Study design	In vitro	In vitro	Prospective clinical study					
	Repair system	Scotch bond Universal (3M All Bond Universal (Bisco) Prime Plus primer	Fabrication technique	Fixed-to-fixed design cantilever design	Clearfil porcelain repair system, Shofu (P and R) repair system				
	Surface treatment	 Polished zirconia All Bond Universal Universal Universal Polished zirconia Single Bond Polished zirconia (control) Polished zirconia (control) Polished zirconia Z-Prime Plus + All Bond Universal Grit-blasted zirconia Single Bond Universal Grit-blasted zirconia All Bond Universal Grit-blasted zirconia All Bond Universal Grit-blasted zirconia Z-Prime Plus + All Bond Universal 	NK	N	Etchant and Primer				
	Manufacturer	IPS e. max ZirCAD, Ivoclar- Vivadent	IPS e.max Press and IPS e.max CAD	CerconBase30, Degudent CerconCeramS, Degudent	1. Bella bond plus (base metal)	2. Ceramco 3 (ceramic)			
	Framework material/ Type of ceramic	Zirconia ceramic	Lithium disilicate	Veneered yttrium-oxide partially stabilized zirconia ceramic	Nickel chromium base metal alloy with ceramic layer				
1. Continued	Author, year	Dos Santos et al., 2019	Gerogianni et al., 2019	Passia <i>et al.</i> , 2019	2019 2019				
Table '	SI. No.	0	7	12	ñ				

Conclusion	 a. Failure is a consequence of crack formation during function 	 b. Repair using resin composite prolongs esthetics and function 	a. The bond strength between zirconia and composite resin can be increased by applying Er, Cr: YSGG laser	applying Er, Cr: YSGG laser b. This laser irradiation can be safely used as a chairside treatment method to repair fractured ceramic restorations			properties and chemical structures	directly affect the surface properties	and bond strength	 a. Surface conditioning with air abrasion and roughening of zirconia showed durable tensile bond strength after repair of zirconia ceramic due to chipping of veneers 			Ceramic repair systems can be used as productive and economical temporary treatment of fractured all ceramic restoration		
Age	60		M			NA				NA			NA		
Number of participants/ samples	÷		60			48				48			06		
Study design	Retrospective case report		In vitro		In vitro			In vitro			In vitro				
Repair system	Estelite Sigma Quick composite repair system		Ceramic Repair N			Filtek Z250			Bifix QM			1. BISCO Intraoral repair kit	2. Cimara and Cimara Zircon Repair System	3. Clearfil Repair System	
Surface treatment	Etchant and Silane		1. Control: Griding	. Control: Griding Short pulse laser . Long pulse laser		1. Control group	2. Etchant	3. Etchant+Silane coupling agent	 A. Sandblasting+Silane coupling agent 	 Silicon carbide paper Air abrasion Special silicon carbide grinder 			Etchant and Silane		
Manufacturer	NR		ICE Zirkon Translucent		1. Vita Enamic		2. Lava Ultimate		Cercon, DeguDent			1. Zirkonzahn	2. In-Ceram Alumina, Vita Zahnfabrik	 Vitablocks for CEREC 	
Framework material/ Type of ceramic	Lithium disilicate based glass ceramic with	feldspathic porcelain veneer	Zirconia ceramic			1. Polymer infiltrated ceramic 2. Resin nano ceramic		Zirconia ceramic		1. Zirconia	2. Alumina	3. Glass ceramic			
Author, year	Garbelotto et al., 2019		Tokar <i>et al.</i> , 2019			Tatar and	Ural, 2018			Libecki <i>et al.</i> ,	/1.07		Kocaağaoğlu <i>et al.</i> , 2017		
No.	4		ň			16			17			8			

	Conclusion	a. The shear bond strength (SBS) of composite resin to porcelain was affected differently by various surface treatments	b. The bonding of	relospathic porcelain is not improved by ceramic particles in the composite resin	a. The resin-ceramic bond depends on both mechanical and chemical retention	 b. For resin adherence to glass ceramic surfaces, a silane solution must always be utilitzed 	 a. Silane has no negative effects on dentin bond strength. cross contamination 	
	Age	M			NA			
	Number of participants/ samples	120			80			
	Study design	In vitro		In vitro	In vitro			
	Repair system	Nh.com and Nc.com resins			Filtek Z350XT	Composite resin		
	Surface treatment	1. Etchant+Silane	2. Air abrasion+Silane	3. Air abrasion	Etchant and Silane		NR	
	Manufacturer	1. VMK95	2. IPS Classic		IPS Empress Esthetic E O ₂	ИА		
	Framework material/ Type of ceramic	1. Vita porcelain	2. Ivoclar	porcelain	Leucite reinforced glass ceramic	Human dentin		
	Author, year	Ozdemir and Yanikoglu, 2017			Sattabanasuk et al., 2017	Chen <i>et al.</i> , 2017		
2 2 2 2	No.	19			20	21		

Table 1. Continued

various surface treatments such as polished surface, air abraded, or ground using a special silicon carbide bur (SiC Grinding Bur), yttrium-aluminum-garnet laser (Neodymium, Erbium, Chromium, Scandium, Gallium, CO₂ laser) treatment were employed across the studies to improve the to increase the surface roughness and bond strength. The repair systems included in the articles were Clearfil Repair, Clearfil Majesty Esthetic, Clearfil Photoposterior, Clearfil porcelain repair system, Shofu (P and R) repair system, Estelite Sigma Quick composite repair system, Cimara, and Cimara Zircon Repair System and BISCO Intraoral repair kit.

The results of the studies included in this review are broadly divided into surface treatment methods and intraoral repair techniques employed in the studies.

3.1 Surface Treatment methods employed in the included studies

Most of the included studies have emphasized different surface treatment methods. An *in vitro* study from Iran compared the effectiveness of new ceramic surface treatments (laser and universal adhesive) with the traditional method for improving the bond strength of composite resin to ceramic during repairs. The group consisting of hydrofluoric (HF) acid, silane, and conventional adhesives had the highest shear bond strength (SBS) (mean: 12.0481 MPa) compared to the traditional adhesive and laser technology group (mean: 2.5766 MPa). HF acid surface treatment produced significantly greater SBS than laser (P < 0.001) (Benli, Kilic *et al.* 2022, Kiomarsi, Jarrah *et al.* 2022). Holler *et al.* compared two distinct surface pretreatment techniques to repair a lithium-disilicate glass-ceramic (LDS) to see how they would react to simulated intraoral circumstances (increased temperature and humidity). Significantly less tensile bond strength (TBS) was produced by higher temperatures and humidity. Self-etching glass-ceramic primer (MEP), however, was a good option for intraoral ceramic repair since it was less susceptible to environmental factors than grit blasting (GBL). The results indicated that a rubber dam should be used during the clinical intraoral repair of lithium-disilicate glass ceramics, especially when utilising GBL (Höller, Belli *et al.* 2022).

Santos *et al.* evaluated the bond strength of universal adhesive systems in comparison to a zirconia primer; and the bonding effectiveness of these materials onto different zirconia surface treatments. Grit-blasted zirconia promoted interlocking of universal adhesive systems to zirconia and had higher bond strength than polished ones (Dos Santos, de Lima *et al.* 2019).

Benli *et al.* assessed the effect of two different lasers in combination with HF etching on the surface roughness of zirconiareinforced lithium silicate (ZLS) ceramics and their SBS to composite resin. The mean SBS values for the HF etching group were highest for neodymium-doped yttrium aluminum garnet (Nd: YAG) laser (17.1 ± 1.65 MPa) and Nd: YAG laser + HF gel group (16.65 ± 1.11 MPa) making them the therapy of choice for the intraoral repair of fractured ceramics (Benli, Kilic *et al.* 2022). Likewise, Hakimaneh *et al.* found heat treatment of silane with erbium-doped yttrium aluminum garnet (Er: YAG) and CO₂ lasers to be effective as HF etching for treating fractured porcelain. However, this treatment failed to improve the micro SBS between feldspathic porcelain and composite resin (Hakimaneh, Shayegh *et al.* 2020). Tokar *et al.* found that erbium, chromium: yttrium scandium gallium garnet (Er, YSGG) laser surface treatments with different pulses can be safely recommended in the treatment of fractured zirconia ceramics and can strengthen the SBS between zirconia and composite resin. Shorter pulse laser irradiation performed better compared to longer pulse rates in terms of mean SBS (Tokar, Polat *et al.* 2019).

Sattabanasuk *et al.* assessed the efficacy of resin adhesion to glass-ceramic surfaces that had previously undergone various treatments and found that silane solution could be used to achieve mechanical and/or chemical retention. The study found that regardless of the tested adhesive, the resin-ceramic bond depended upon both mechanical and chemical retention. The authors suggested that adding a silane monomer to the adhesive formulation may not be the best way to achieve silanization and hence recommend regularly applying a silane solution to a glass-ceramic surface to ensure resin adherence (Sattabanasuk, Charnchairerk *et al.* 2017).

Polat *et al.* compared the effectiveness of Er, Cr: YSGG laser with short and long pulse durations to different surface roughening techniques for repairing zirconia ceramics with various surface configurations and found there were no discernible variations among sandblasting and Er, Cr: YSGG laser treatments (Polat, Tokar *et al.* 2021). Tatar and Ural investigated surface treatments for chipping to reduce the problems related to bonding between hybrid materials and composites and found that the most effective method was air abrasion with silica-coated aluminum oxide (Tatar and Ural 2018). A similar study by Libecki *et al.* where the aim was to check the efficacy of different surface treatment options (air abraded, polished surface, or ground using a special silicon carbide bur), reported that the TBS is high when the ceramic is conditioned with air abrasion or roughened with silicon carbide bur (Libecki, Elsayed *et al.* 2017). Ozdemir and Yanikoglu assessed the SBS of nano-hybrid and nano-ceramic composite resins to feldspathic porcelain (Vita and Ivoclar) and found the latter to possess lower SBS compared with the former (Ozdemir and Yanikoglu 2017). A study by

Chen *et al.* evaluated if silane contamination of dentin impacts the binding strength of the tissue and found that there were no adverse effects on SBS due to contamination of dentin with silane before etching (Chen, Hammond *et al.* 2017).

3.2 Intraoral repair techniques in the included studies

Various intraoral techniques employed in the studies included in the review are listed below. Passia *et al.* evaluated the long-term outcome of posterior all-ceramic FDPs made from veneered zirconia ceramic with either a fixed-to-fixed (FF) or a cantilever design (CA). The cumulative 13-year survival rate was 43.2% (FF) (CI: 22.8–66.2%) and 52.5% (CA) (CI: 32.5–71.8); and success rate was 29.5% (FF) (CI:12.1–55.9%) and 22.5% (CA) (CI: 7.9–49.3%) respectively. The survival rates were comparable and failure rates were high, irrespective of the design (Passia, Chaar *et al.* 2019). An in vitro study analyzed the long-term performance of fabrication techniques on anterior teeth and found that the pressed groups (923.7 N) exhibited significantly higher fracture resistance and crown strength than the milled groups (797.5 N), (p = 0.0002) (Gerogianni, Lien *et al.* 2019). In a study by Sanal and Kilinc, SBS and color stability of four ceramic veneers (VITAVM 9, VITA VM 13, VITA VMK 95, and IPS e.max Ceram) treated with different repair systems (Vertise Flow, Fusio Liquid Dentin, Constic, and BISCO intraoral repair kit + Filtek Supreme) was examined. The findings of the study indicated that Constic self-adhesive composite resin had the lowest color stability value, but that there was no discernible difference between it and the other repair methods (Sanal and Kilinc 2020).

A study by Meirelles *et al.*, reported five-year survival of intraoral repair of cracked porcelain veneered zirconia framework restoration with composite resin reconstruction, suggesting that it could be a suitable alternative therapy (Meirelles, da Rocha *et al.* 2020). Gul and Uygun evaluated the micro-TBS of the nanocomposite resin to three CAD/CAM blocks utilizing various intraoral repair procedures. In comparison to the other repair methods examined, the Cimara System, Clearfil Repair, and Porcelain Repair systems significantly improved (p<0.05) the binding strength of nanohybrid resin composite to all CAD/CAM blocks (Gul and Altnok-Uygun 2020). A case report by Mesquita *et al.* reported that proper execution of the direct veneering strategies yields fast and effective solutions to fracture or chipping of the veneering ceramic, without the need to replace the prosthesis. The durability of the repair relies on the quality of the interface created and the clinician's hold on the adhesive procedures (Mesquita, Al-Haj Husain *et al.* 2021).

Yadav *et al.* reported that the ClearfilTM repair method had higher SBS (29.16 Mpa) than Primer and Cera resin bond repair material for cohesive fractures, whereas the latter had higher SBS (27.23 Mpa) for adhesive fractures compared to ClearfilTM repair method in metal-ceramic restorations (Yadav, Dabas *et al.* 2019). The retrospective analysis conducted by Gabelotto *et al.* discussed the clinical phases of an intraoral composite resin repair and a fractographic examination of the failure reasons for the chipping of the veneering ceramic of an anterior single crown. Fractographic analysis revealed that failure was a result of crack development during function, most likely brought on by an occlusal interference, and thereby improved the knowledge of the origin of failure to avoid failures in the future (Garbelotto, Fukushima *et al.* 2019).

Discussion

The current review aimed to summarize the available literature on the effectiveness of intraoral repair techniques for ceramic fractures. Twenty-one relevant studies published in English between 2016 and 2022 which discussed various surface treatments and intraoral repair systems were included in the review.

It is a common observation in a dental practice that despite having a high success rate, chipping or fracture of the veneering ceramic is the main cause of clinical failure for veneered zirconia-based restorations (Pjetursson, Sailer *et al.* 2015). Given the complexities of veneered zirconia-based restorations, clinicians and researchers have explored a variety of intraoral repair techniques to treat the chipping and protect the intact structures. Under appropriate conditions, intraoral repair acts as a potential therapy option. Dental professionals now have a great deal of interest in the scientific basis, therapeutic methods, and clinical effectiveness of the intraoral repair of cracked veneered zirconia-based restorations. Reviewing the intraoral repair of veneered zirconia-based restorations would improve practitioners' understanding of the advised procedures when zirconia repair is required (Agingu, Zhang *et al.* 2018).

Understanding the complexities of porcelain fractures is the first step. Porcelain fractures can be static, cohesive, or adhesive. The material used for framework fabrication determines the repair procedure (Aslam, Hassan *et al.* 2018). Regardless of their high 5-year survival rate of 90.4% (95% CI: 84.8–94.0%), porcelain-veneered zirconia FDPs can eventually crack and get chipped off. This is fundamentally due to the loss of adhesion between zirconia and veneering ceramics (Pjetursson, Sailer *et al.* 2015). A variety of factors can cause the fracture of veneered porcelain on metal-ceramic crowns, which include lack of sufficient porcelain framework support, intra-ceramic flaws, or parafunctional occlusion (Haselton, Diaz-Arnold *et al.* 2001). Porcelain fracture can manifest clinically with no metal substrate exposure, modest metal substrate exposure, or significant metal exposure. Although fabricating a new crown

seems desirable, it is not always possible. In such cases, the option of intraoral restoration is deemed of immense importance (Haselton, Diaz-Arnold *et al.* 2001).

Before the build-up of the veneer layer, a succession of thermal sintering cycles and accompanying cooling processes are used to prepare crowns and FPDs. The matching of thermal expansion between the porcelain and the underlying framework, whether metal or ceramic, is crucial to avoid breaking following the firing. Delamination of the porcelain can occur when the coefficient of thermal expansion (CTE) of the framework is significantly higher than that of the porcelain and substructure to eliminate any stresses in the layered porcelain (Aboushelib, Kleverlaan *et al.* 2006, Swain 2009). Fracture is a potential risk for veneered ceramics with such residual stress. A tensile stress zone can form below and at the edge of the contact surface of the veneer layer resulting from the combination of compressive residual stress and local stress brought on by mastication (Taskonak, Mecholsky *et al.* 2005). Several elements influence the development of thermally induced residual stress and contribute to porcelain chipping which includes the veneer's overall thickness, cooling rate, and shape. Guazzato *et al.* (2010) found that rapid cooling and increased porcelain veneer thickness increase the risk of crack occurrence (Guazzato, Walton *et al.* 2010). Zirconia may also crack due to the volume expansion (3–4%) occurring during the thermal tempering at high temperatures, which is done to facilitate tetragonal to monoclinic transition (Piconi and Maccauro 1999).

Meeting the requirements for repairing a failed restoration is the next essential step. The establishment of a permanent bond between the previous restoration and the new repair material is the key to a successful repair. Therefore, choosing the right adhesive resin and restorative substance, as well as adequate surface conditioning of the substrate, is important. To increase bond strength, the surface is roughened using a variety of surface preparation processes (Duzyol, Sagsoz *et al.* 2016). Acid etching using hydrofluoric acid (HF) is an optimal approach for roughening feldspar ceramic surfaces for resin composite bonding. In comparison with HF treatment alone, the introduction of a silane coupling agent after HF results in stronger resistant bonds. Further, newer surface modifications, such as surface abrading airborne particles, have been developed with advancements in adhesive technology. The initial step in this approach is air abrasion using aluminum oxide particles. Increased resin composite-porcelain bond strengths are reportedly achieved by sandblasting the porcelain's surface with aluminum oxide particles (35–250 μ m) (Duzyol, Sagsoz *et al.* 2016). After air abrasion, chemical adhesion can be generated using specialized primers that interact with a material's surface. To chemically bind the inorganic filler particles to the resin matrix, the most commonly used primer is a silane coupling agent, which is also employed in the construction of composites (Loomans and Özcan 2016).

The wettability of the composite to be utilized as a repair material is increased by applying intermediate adhesive resin to the silanized surface. It is often recommended, but not required, to mix identical composite materials when doing composite-composite repairs due to the variable effects of different substrate materials (Baur and Ilie 2013). Usage of adhesive resin, silanization, and HF acid etching, adhesion to glassy matrix ceramics has been thoroughly established. Optimal surface conditioning of indirect composite restorations can be achieved by using airborne particle abrasion followed by an adhesive resin with a silane coupling agent (Loomans and Özcan 2016).

In the current review, HF etching in combination with laser treatment or silane and traditional adhesive was found to strengthen the link between porcelain and composite resin (Hakimaneh, Shayegh *et al.* 2020, Benli, Kilic *et al.* 2022, Kiomarsi, Jarrah *et al.* 2022). However, durable TBS was observed when surface treatment with air abrasion or roughening the zirconia surface with a silicon carbide bur was offered for the repair of zirconia ceramic after chipping of its veneers (Libecki, Elsayed *et al.* 2017).

Conclusion

With the limitations of this narrative review, we can conclude that intraoral repair of ceramic fractures offers esthetics and comfort to patients when a restoration cannot be removed or changed. The current review indicated that the best technique to fix chipping in a complex made of zirconia core and veneering ceramic is to treat the veneering ceramic with HF before covering the zirconia core ceramic with silica. Both ceramic substrates must then be covered with adhesive resin and silane. The intraoral repair utilizing resin-based composite materials has significant advantages since it retains most of the restoration, prevents needless loss of healthy tooth structure, and is a quick and simple, reasonably priced procedure with no need for repeated sessions. The skills of the clinicians in using these tools and techniques as well as adherence to prescribed procedures and protocols are crucial to the effectiveness of these treatments.

Data availability

No data are associated with this article.

References

Aboushelib MN, Kleverlaan CJ, Feilzer AJ: Microtensile bond strength of different components of core veneered all-ceramic restorations. Part II: Zirconia veneering ceramics. Dent. Mater. 2006; 22(9): 857–863. Publisher Full Text

Agingu C, Zhang C-Y, Jiang N-W, et al.: Intraoral repair of chipped or fractured veneered zirconia crowns and fixed dental prosthesis: clinical guidelines based on literature review. J. Adhes. Sci. Technol. 2018; **32**: 1–13.

Aslam A, Hassan S, Nayyer M, et al.: Intra-oral Repair Protocols for Fractured Metal-Ceramic Restorations - Literature Review. South African dental journal. Suid Afrikaanse tandarts tydskrif. 2018; 73.

Baur V, Ilie N: Repair of dental resin-based composites. *Clin. Oral Investig.* 2013; **17**(2): 601–608.

PubMed Abstract | Publisher Full Text

Benli M, Kilic EHH, Gumus BE, et al.: Effects of Various Laser Treatments on Surface Characterization and Repair Bond Strength of Zirconia-Reinforced Lithium Silicate Ceramics. Int. J. Prosthodont. 2022; PubMed Abstract | Publisher Full Text

Chen L, Hammond BD, Alex G, *et al.*: Effect of silane contamination on dentin bond strength. J. Prosthet. Dent. 2017; **117**(3): 438–443. PubMed Abstract | Publisher Full Text

Dos Santos RA, de Lima EA, Mendonça LS, *et al.*: **Can universal adhesive** systems bond to zirconia? *J. Esthet. Restor. Dent.* 2019; **31**(6): 589–594. PubMed Abstract | Publisher Full Text

Duzyol M, Sagsoz O, Polat Sagsoz N, et al.: The Effect of Surface Treatments on the Bond Strength Between CAD/CAM Blocks and Composite Resin. J. Prosthodont. 2016; 25(6): 466–471. PubMed Abstract | Publisher Full Text

Garbelotto LGD, Fukushima KA, Ozcan M, *et al.*: **Chipping of veneering ceramic on a lithium disilicate anterior single crown: Description of repair method and a fractographic failure analysis.** *J. Esthet. Restor. Dent.* 2019; **31**(4): 299–303.

PubMed Abstract | Publisher Full Text

Gerogianni P, Lien W, Bompolaki D, et al.: Fracture Resistance of Pressed and Milled Lithium Disilicate Anterior Complete Coverage Restorations Following Endodontic Access Preparation. J. Prosthodont. 2019; 28(2): 163–170.

PubMed Abstract | Publisher Full Text

Guazzato M, Walton TR, Franklin W, et al.: Influence of thickness and cooling rate on development of spontaneous cracks in porcelain/ zirconia structures. Aust. Dent. J. 2010; 55(3): 306–310. PubMed Abstract | Publisher Full Text

Gul P, Altınok-Uygun L: **Repair bond strength of resin composite to three aged CAD/CAM blocks using different repair systems**. J Adv Prosthodont. 2020; **12**(3): 131–139.

Publisher Full Text

Hakimaneh SMR, Shayegh SS, Ghavami-Lahiji M, et al.: Effect of Silane Heat Treatment by Laser on the Bond Strength of a Repair Composite to Feldspathic Porcelain. J. Prosthodont. 2020; 29(1): 49–55. PubMed Abstract | Publisher Full Text

Hammond B, Swift EJ, Brackett W: INTRAORAL REPAIR OF FRACTURED CERAMIC RESTORATIONS. J. Esthet. Restor. Dent. 2009; 21: 275–284. PubMed Abstract | Publisher Full Text

Haselton DR, Diaz-Arnold AM, Dunne JT Jr: Shear bond strengths of 2 intraoral porcelain repair systems to porcelain or metal substrates. J. Prosthet. Dent. 2001; 86(5): 526-531. Publisher Full Text

Publisher Full Text

Höller B, Belli R, Petschelt A, et al.: Influence of Simulated Oral Conditions on Different Pretreatment Methods for the Repair of Glass-Ceramic Restorations. J. Adhes. Dent. 2022; 24(1): 57–66.

Kimmich M, Stappert CF: Intraoral treatment of veneering porcelain chipping of fixed dental restorations: a review and clinical application. J. Am. Dent. Assoc. 2013; 144(1): 31–44. PubMed Abstract | Publisher Full Text

Kiomarsi N, Jarrah A, Chiniforoush N, et al.: Effect of surface treatment with laser on repair bond strength of composite resin to ceramic. Dent Res J (Isfahan). 2022; 19: 30.

PubMed Abstract

Kocaağaoğlu H, Manav T, Albayrak H: In Vitro Comparison of the Bond Strength between Ceramic Repair Systems and Ceramic Materials and Evaluation of the Wettability. J. Prosthodont. 2017; 26(3): 238–243. PubMed Abstract I Publisher Full Text

Libecki W, Elsayed A, Lehmann F, et al.: Efficacy of Different Surface Treatments for Intraoral Repair of Veneered Zirconia Frameworks.

J. Adhes. Dent. 2017; 19(4): 323–329. PubMed Abstract | Publisher Full Text

Loomans B, Özcan M: Intraoral Repair of Direct and Indirect Restorations: Procedures and Guidelines. Oper. Dent. 2016; 41(S7): S68–s78.

PubMed Abstract | Publisher Full Text

Meirelles PD, da Rocha LS, Pecho OE, *et al.*: **Intraoral repair of a chipped porcelain-zirconia restoration**. *J. Esthet. Restor. Dent.* 2020; **32**(5): 444–450.

PubMed Abstract | Publisher Full Text

Mesquita AMM, Al-Haj Husain N, Molinero-Mourelle P, et al.: An Intraoral Repair Method for Chipping Fracture of a Multi-unit Fixed Zirconia Reconstruction: A Direct Dental Technique. Eur. J. Dent. 2021; 15(1): 174–178.

PubMed Abstract | Publisher Full Text

Özcan M, Volpato CAM: Intra-oral repair technique for ceramic fracture using direct resin composite. 2017.

Ozdemir H, Yanikoglu ND: The Bond Strength of Nanohybrid and Nanoceramic Composites to Feldspathic Porcelain. Contemp. Clin. Dent. 2017; 8(4): 558–564.

PubMed Abstract | Publisher Full Text

Passia N, Chaar MS, Kern M: Outcome of posterior fixed dental prostheses made from veneered zirconia over an observation period of up to 13 years. J. Dent. 2019; 86: 126–129. PubMed Abstract | Publisher Full Text

Piconi C, Maccauro G: **Zirconia as a ceramic biomaterial**. *Biomaterials*. 1999; **20**(1): 1–25.

Publisher Full Text

Pjetursson BE, Sailer I, Makarov NA, et al.: All-ceramic or metal-ceramic tooth-supported fixed dental prostheses (FDPs)? A systematic review of the survival and complication rates. Part II: Multiple-unit FDPs. Dent. Mater. 2015; 31(6): 624-639.

PubMed Abstract | Publisher Full Text

Polat S, Tokar E, Asar NV, et al.: Evaluation of Efficacy of Various Surface Conditioning Methods on the Repair Bond Strength of Composite to Different Fracture Types of Zirconia Ceramics. Scanning. 2021; 2021: 5537761.

Rosentritt M, Steiger D, Behr M, et al.: Influence of substructure design and spacer settings on the in vitro performance of molar zirconia crowns. J. Dent. 2009; **37**(12): 978–983.

Publisher Full Text

Sanal FA, Kilinc H: Evaluating Ceramic Repair Materials in Terms of Bond Strength and Color Stability. Int. J. Prosthodont. 2020; 33(5): 536–545.

PubMed Abstract | Publisher Full Text

Sattabanasuk V, Charnchairerk P, Punsukumtana L, et al.: Effects of mechanical and chemical surface treatments on the resin-glass ceramic adhesion properties. J. Investig. Clin. Dent. 2017; 8(3): e12220. PubMed Abstract | Publisher Full Text

Swain MV: Unstable cracking (chipping) of veneering porcelain on allceramic dental crowns and fixed partial dentures. *Acta Biomater*, 2009; 5(5): 1668–1677.

PubMed Abstract | Publisher Full Text

Taskonak B, Mecholsky JJ Jr, Anusavice KJ: **Residual stresses in bilayer dental ceramics.** *Biomaterials*. 2005; **26**(16): 3235–3241. **PubMed Abstract | Publisher Full Text**

Tatar N, Ural C: Repair Success of Two Innovative Hybrid Materials as a Function of Different Surface Treatments. Int. J. Prosthodont. 2018; 31(3): 267–270.

PubMed Abstract | Publisher Full Text

Tokar E, Polat S, Ozturk C: **Repair bond strength of composite to Er,Cr: YSGG laser irradiated zirconia and porcelain surfaces.** *Biom. J.* 2019; **42**(3): 193–199.

Publisher Full Text

Vagropoulou GI, Klifopoulou GL, Vlahou SG, et al.: **Complications and** survival rates of inlays and onlays vs complete coverage restorations: A systematic review and analysis of studies. J. Oral Rehabil. 2018; **45**(11): 903–920.

PubMed Abstract | Publisher Full Text

Yadav JS, Dabas N, Bhargava A, et al.: Comparing two intraoral porcelain repair systems for shear bond strength in repaired cohesive and adhesive fractures, for porcelain-fused-to-metal restorations: An in vitro study. J. Indian Prosthodont Soc. 2019; **19**(4): 362–368. PubMed Abstract | Publisher Full Text

Open Peer Review

Current Peer Review Status: 🗹 🗹 ?

Version 1

Reviewer Report 07 January 2025

https://doi.org/10.5256/f1000research.138970.r344694

© **2025 Fulzele P.** This is an open access peer review report distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.



Punit Fulzele 匝

SPDC, Datta Meghe Institute of Higher Education & Research, Wardha, Maharashtra, India

This review addresses the intraoral repair of fractured dental ceramics, a common and clinically significant issue in dental practice. The authors conducted a non-structured PubMed search for articles published in English between 2017 and 2022, identifying 21 relevant studies. This review considers various techniques and ceramic types to provide a comprehensive overview of modern repair strategies for ceramic fractures and current repair protocols for different fracture types and core materials. It is a valuable resource for research and clinical practice due to its practical relevance and accessibility. Although the clinical studies were limited to 50 patients, the conclusions must be interpreted cautiously. There is an inconsistency in the reported timeframe for the included studies. Two critical aspects have not been discussed: the age of the restoration and the impact it has on the repair prognosis-surface pretreatment with plasma for improved bond stability. The review's conclusions, while logical, are not fully supported by the included articles. There is, however, a well-structured summary of existing practices and recommendations for managing intraoral ceramic repairs. Despite some limitations, it offers dental professionals a valuable resource for understanding and implementing current repair strategies. Additional clinical data and the additional aspects mentioned could be included in future reviews to give a more comprehensive topic analysis.

Is the topic of the review discussed comprehensively in the context of the current literature?

Yes

Are all factual statements correct and adequately supported by citations?

Yes

Is the review written in accessible language?

Yes

Are the conclusions drawn appropriate in the context of the current research literature?

Partly

Competing Interests: No competing interests were disclosed.

Reviewer Expertise: CADCAM, Digital technologies, Dentistry.

I confirm that I have read this submission and believe that I have an appropriate level of expertise to confirm that it is of an acceptable scientific standard, however I have significant reservations, as outlined above.

Reviewer Report 02 January 2025

https://doi.org/10.5256/f1000research.138970.r344693

© **2025 Delgado-Ruiz R.** This is an open access peer review report distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

? Rafael Delgado-Ruiz

 ¹ State University of New York at Stony Brook, Stony Brook, USA
 ² Prosthodontics and Digital Technology, Stony Brook University, School of Dental Medicine, Stony Brook, New York, USA

The authors conducted a review of techniques for the intraoral repair of fractured dental ceramics, addressing a relevant and clinically significant topic for the journal's audience. Fractured ceramics represent a common complication in dental practice, often requiring effective clinical intervention and repair.

The authors performed a non-structured search on PubMed for articles published in English between 2017 and 2022 related to intraoral ceramic repair, identifying 21 articles. Of these, 17 were in-vitro studies, 3 were case reports, and 1 was a prospective clinical study. However, the clinical data is limited, as the case reports and the prospective study together account for only 50 patients. Given this lack of robust clinical evidence, the conclusions of the manuscript should be interpreted with caution.

In addition, the second part of the conclusions "The intraoral repair utilizing resin-based composite materials has significant advantages since it retains most of the restoration, prevents needless loss of healthy tooth structure, and is a quick and simple, reasonably priced procedure with no need for repeated sessions. The skills of the clinicians in using these tools and techniques as well as adherence to prescribed procedures and protocols are crucial to the effectiveness of these treatments." although logical, is not supported by the articles included in this review.

Is the topic of the review discussed comprehensively in the context of the current literature?

Yes

Are all factual statements correct and adequately supported by citations?

Yes

Is the review written in accessible language?

Yes

Are the conclusions drawn appropriate in the context of the current research literature? Partly

Competing Interests: No competing interests were disclosed.

Reviewer Expertise: Prosthodontics, CAD-CAM, Digital technologies, Optical Scanners, Dental Implants, Thermography

I confirm that I have read this submission and believe that I have an appropriate level of expertise to confirm that it is of an acceptable scientific standard, however I have significant reservations, as outlined above.

Reviewer Report 03 December 2024

https://doi.org/10.5256/f1000research.138970.r344687

© **2024 Pott P.** This is an open access peer review report distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.



Philipp-Cornelius Pott 匝

Hannover Medical School, Hannover, Germany

The authors have addressed a clinically highly relevant topic. The summarized literature is well suited to provide an overview of modern strategies for the repair of ceramic fractures. Particularly noteworthy is the fact that the authors consider not only various repair techniques but also various ceramics in a differentiated way. This nicely highlights the fact that not every repair strategy can be applied equally to all materials or material combinations. I also particularly like the fact that the authors address possible causes of damage to restorations at the beginning of the discussion.

In the methodology section, chapter 2.1, it is stated that studies published between January 2017 and August 2022 have been included. However, a different time period (2016 to 2022) is given in the first chapter of the discussion. This is probably just a typo, which should be easy to correct. Nevertheless, a fairly extensive presentation of intraoral ceramic repair has already been made here, but unfortunately I miss two important aspects that should be added to the discussion: 1. Age of the restoration to be repaired.

Unfortunately, silicate ceramics absorb moisture over time. This moisture absorption cannot be reversed intraorally. Accordingly, this reduces the prognosis for a secure, stable bond. In zirconium dioxide ceramics, so-called low-temperature degradation occurs over time under the conditions prevailing intraorally (Borchers et al Ref 1; Kohorst et al. Ref 2). This also reduces the

long-term prognosis of a restoration that may need to be repaired.

2. <u>Surface pretreatment with plasma.</u>

The application of cold argon plasma to ceramic surfaces, for example, increases hydrophilicity and thus improves wettability with adhesives, thereby increasing the long-term stability of the ceramic-composite bonds (Pott et al. ref 3). Corresponding application devices are also available for dentistry.

References

1. Borchers L, Stiesch M, Bach FW, Buhl JC, et al.: Influence of hydrothermal and mechanical conditions on the strength of zirconia.*Acta Biomater*. 2010; **6** (12): 4547-52 PubMed Abstract | Publisher Full Text

2. Kohorst P, Borchers L, Strempel J, Stiesch M, et al.: Low-temperature degradation of different zirconia ceramics for dental applications.*Acta Biomater*. 2012; **8** (3): 1213-20 PubMed Abstract | Publisher Full Text

3. Pott PC, Syväri TS, Stiesch M, Eisenburger M: Influence of nonthermal argon plasma on the shear bond strength between zirconia and different adhesives and luting composites after artificial aging *J Adv Prosthodont*. 2018; **10** (4): 308-314 PubMed Abstract | Publisher Full Text

Is the topic of the review discussed comprehensively in the context of the current literature?

Yes

Are all factual statements correct and adequately supported by citations?

Yes

Is the review written in accessible language?

Yes

Are the conclusions drawn appropriate in the context of the current research literature? $\ensuremath{\mathsf{Yes}}$

Competing Interests: No competing interests were disclosed.

Reviewer Expertise: dentistry, adhesive dentistry, adhesion to ceramic materials and metals, prosthodontics, all-ceramics

I confirm that I have read this submission and believe that I have an appropriate level of expertise to confirm that it is of an acceptable scientific standard.

Reviewer Report 28 November 2022

https://doi.org/10.5256/f1000research.138970.r155374

© **2022 Ghanem L.** This is an open access peer review report distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.



Lomaya Ghanem

Fixed Prosthodontics Department, Faculty of Dentistry, Misr International University, Cairo, Egypt

Intraoral repair of fractured veneering ceramic is a very relevant, economic and conservative clinical approach. The review herein clearly exhibits the fracture types, their conforming repair protocol in relevance to the restoration core material (metal or ceramic), highlighting procedures and materials used. The herein review is supported with literature consistent with current research. Language, context, and drawn conclusions: clear

It furnishes a practical source for research, and provides an accessible overview and understanding of the topic, as well as recommendations for management of intraoral repair using the existing practices.

Is the topic of the review discussed comprehensively in the context of the current literature?

Yes

Are all factual statements correct and adequately supported by citations? Yes

Is the review written in accessible language?

Yes

Are the conclusions drawn appropriate in the context of the current research literature? $\ensuremath{\mathsf{Yes}}$

Competing Interests: No competing interests were disclosed.

Reviewer Expertise: Fixed Prosthdodontics, ceramics, pressing, bonding, CADCAM.

I confirm that I have read this submission and believe that I have an appropriate level of expertise to confirm that it is of an acceptable scientific standard.

The benefits of publishing with F1000Research:

- Your article is published within days, with no editorial bias
- You can publish traditional articles, null/negative results, case reports, data notes and more
- The peer review process is transparent and collaborative
- Your article is indexed in PubMed after passing peer review
- Dedicated customer support at every stage

For pre-submission enquiries, contact research@f1000.com

F1000 Research