

SCIENTIFIC REPORTS



OPEN

Cu₂ZnSnS₄/MoS₂-Reduced Graphene Oxide Heterostructure: Nanoscale Interfacial Contact and Enhanced Photocatalytic Hydrogen Generation

Enna Ha¹, Wei Liu¹, Luyang Wang¹, Ho-Wing Man¹, Liangsheng Hu¹, Shik Chi Edman Tsang², Chris Tsz-Leung Chan¹, Wai-Ming Kwok¹, Lawrence Yoon Suk Lee¹ & Kwok-Yin Wong¹

Hydrogen generation from water using noble metal-free photocatalysts presents a promising platform for renewable and sustainable energy. Copper-based chalcogenides of earth-abundant elements, especially Cu₂ZnSnS₄ (CZTS), have recently arisen as a low-cost and environment-friendly material for photovoltaics and photocatalysis. Herein, we report a new heterostructure consisting of CZTS nanoparticles anchored onto a MoS₂-reduced graphene oxide (rGO) hybrid. Using a facile two-step method, CZTS nanoparticles were *in situ* grown on the surface of MoS₂-rGO hybrid, which generated high density of nanoscale interfacial contact between CZTS and MoS₂-rGO hybrid. The photoexcited electrons of CZTS can be readily transported to MoS₂ through rGO backbone, reducing the electron-hole pair recombination. In photocatalytic hydrogen generation under visible light irradiation, the presence of MoS₂-rGO hybrids enhanced the hydrogen production rate of CZTS by 320%, which can be attributed to the synergistic effect of increased charge separation by rGO and more catalytically active sites from MoS₂. Furthermore, this CZTS/MoS₂-rGO heterostructure showed much higher photocatalytic activity than both Au and Pt nanoparticle-decorated CZTS (Au/CZTS and Pt/CZTS) photocatalysts, indicating the MoS₂-rGO hybrid is a better co-catalyst for photocatalytic hydrogen generation than the precious metal. The CZTS/MoS₂-rGO system also demonstrated stable photocatalytic activity for a continuous 20 h reaction.

Semiconductor nanomaterials possess several useful intrinsic properties, such as morphology-dependent optical properties, capability of converting solar energy into either electrical or chemical energy, and large surface area-to-volume ratio, which have triggered tremendous research efforts in developing new class of materials in the last decade, especially in the fields of photocatalysis^{1–4}, solar cells^{5,6}, and light emitting devices⁷. Oxide semiconductors, which have been widely used as a light absorbing material, usually have a wide band gap due to the low lying valence band (VB) composed of oxygen orbitals^{8–12}. This poses a limit on the useful absorption range for exciton generation and thus lowers the power conversion efficiency in many cases of oxides. Sulfide materials, on the other hand, possess narrower band gaps than oxides, and have recently gained much research interests as alternatives for oxides^{13–15}. Particularly, a quaternary copper-based chalcogenide Cu₂ZnSnS₄ (CZTS) has shown a number of advantages in harvesting and harnessing the solar energy. The low band gap of around 1.5 eV makes CZTS a suitable light absorbing material for both ultra-violet (UV) and visible lights. Moreover, all the components in CZTS are earth abundant, low-cost, and less-toxic, making it a sustainable clean energy converter^{16–18}. In addition to its application as a light absorber in photovoltaic devices, CZTS has been also engaged in the photocatalytic hydrogen generation as an effective catalyst and demonstrated better catalytic performance and stability than commercialized CdS and N-doped TiO₂ for visible light hydrogen production¹⁹. Precious metals

¹Department of Applied Biology and Chemical Technology and the State Key Laboratory of Chirosciences, The Hong Kong Polytechnic University, Hung Hom, Kowloon, Hong Kong SAR, China. ²Wolfson Catalysis Centre, Department of Chemistry, University of Oxford, Oxford, OX1 3QR, UK. Correspondence and requests for materials should be addressed to L.Y.S.L. (email: lawrence.y.s.lee@polyu.edu.hk) or K.Y.W. (email: kwok-yin.wong@polyu.edu.hk)




Figure 1. Typical (a) TEM and (b), (c) high-resolution TEM images of as-prepared CZTS/MoS₂-rGO composites.

with high catalytic activity and surface plasmon resonance effect, such as Pt and Au, have been decorated on or incorporated with CZTS as a co-catalyst, which resulted in a significant enhancement in photocatalytic hydrogen production^{20–22}. However, the scarcity and high cost of these noble metals void their competitiveness and hamper their widespread use in industry. It would be much advantageous if the catalytic efficiency of CZTS can be improved by coupling with other low cost but high performance materials through a delicate interfacial design.

Constructing heterostructure stands out as an effective way to transfer the excitons away from the recombination sites and increase the number of active sites for catalytic processes^{23–25}. Moreover, nanoscale interfacial contact in the heterostructures has also been proved as a fast and shorter channel for exciton transportation, which further inhibits the recombination^{26–28}. The nanoscale interfacial contact can be formed through epitaxial growth, where one composite grows on the other crystalline substrate through the same structural orientation²⁹. In the NaTaO₃/Ta₂O₅ heterostructure, NaTaO₃ was grown epitaxially along [121] direction on the (110) Ta₂O₅ crystal plane³⁰. Compared to the single components, the photocatalytic hydrogen generation yield of this heterostructure has more than doubled. It was also reported that the heterostructure of CdS and ZnIn₂S₄ with mismatched lattice formed a nanointerface through dangling bonds³¹. The resulting helical CdS/ZnIn₂S₄ has demonstrated three-fold enhancement in the photocurrent intensity. These superior properties arisen from nanoscale interfacial contact have inspired us to develop the CZTS-based heterostructures.

Two dimensional materials, especially graphene and MoS₂, possess unique properties of large surface area, fast electron mobility, and superior catalytic ability, all of which make them highly attractive for numerous applications^{32–37}. In the study of Bi₂WO₆-MoS₂-reduced graphene oxide (rGO) heterostructure, MoS₂-rGO hybrid has shown the confined space effect for the synthesis of Bi₂WO₆ and the nanoscale interfacial contact results in the enhanced photocatalytic properties. By coupling rGO and MoS₂ with CZTS into a robust heterostructure with nanoscale interfacial contacts, we expect pronounced enhancements in photocatalytic performance of CZTS, which is currently not as competitive as other systems. Herein, we report a simple method of incorporating CZTS nanoparticles with rGO, few-layer MoS₂, and MoS₂-rGO hybrids, and their photocatalytic performances in hydrogen generation under visible light irradiation. We found that the photocatalytic activity of CZTS/MoS₂-rGO heterostructure outperforms those of many other hydrogen photocatalysts based on earth abundant elements reported in the literature, and it also showed excellent long-term stability^{38–40}.

Results and Discussion

The CZTS/MoS₂-rGO heterostructure was prepared by a two-step reaction. In the first step, MoS₂-rGO hybrid was synthesized by hydrothermal reaction where few-layered MoS₂ nanosheets were constructed in the presence of graphene oxide. In the following colloidal synthesis, Cu-Zn-Sn-oleylamine precursors and sulfur source were nucleated and grown to nanoparticles in the presence of MoS₂-rGO hybrids. Figure 1 displays typical transmission electron microscopic (TEM) images of as-synthesized CZTS/MoS₂-rGO heterostructure where spherical CZTS nanoparticles were in nanoscale interfacial contact with MoS₂-rGO hybrid substrates. High-resolution TEM images of CZTS/MoS₂-rGO heterostructure, shown in Fig. 1(b) and (c), clearly reveal the lattice fringes from each component and the interface, indicating their high degree of crystallinity and close contact. The CZTS nanoparticles are slightly polydispersed with most of the nanoparticle sizes falling in the range of 5–20 nm (Fig. S1 in the Supporting Information). The average particle size is 10.5 ± 2.7 nm. MoS₂ displays a multi-layered structure with an interlayer spacing of 0.62 nm which corresponds to the (002) planes of hexagonal MoS₂. The measured interplanar d-spacing of 0.32 nm in the light-colored area can be ascribed to the (002) plane of kesterite




Figure 2. Powder XRD patterns of as-synthesized CZTS, MoS₂-rGO, and CZTS/MoS₂-rGO composite.




Figure 3. Raman spectra of as-synthesized (a) GO and (b) CZTS/MoS₂-rGO composite. Inset shows the comparison of Raman spectra of (b) CZTS/MoS₂-rGO, (c) MoS₂, and (d) CZTS in the region of 250 to 500 cm⁻¹.

CZTS. In the synthetic procedure, MoS₂-rGO hybrid and sulfur were dispersed in oleylamine and sonicated. It is well known that sulfur reacts with oleylamine and produces alkylammonium polysulfides during the sonication⁴¹. At the same time, the sulfur ions bind to the exposed Mo atoms of MoS₂ and defective sites of rGO through covalent binding⁴². Upon heating at high temperature, H₂S is *in situ* produced and reacts with the metal precursors to form CZTS on the surface of MoS₂-rGO hybrid⁴³. The co-existence of four constituent elements in CZTS as well as Mo was confirmed by energy dispersive spectroscopy (EDS) and elemental mapping (Figs S2 and S3). TEM images of CZTS, MoS₂, GO, CZTS/MoS₂, CZTS/rGO, and MoS₂-rGO hybrids were also taken and shown in Fig. S4 for comparison.

X-ray powder diffraction (XRD) patterns obtained from as-synthesized MoS₂-rGO, CZTS, and CZTS/MoS₂-rGO are shown in Fig. 2. XRD results confirmed that the presence of MoS₂ and rGO did not alter the crystal phase of CZTS nor produce any binary/tertiary byproducts. All the diffraction peaks of the heterostructure are well indexed according to the kesterite phase of CZTS. There was, however, no characteristic diffraction peaks for MoS₂ and carbon species observed because of the small weight ratio in the heterostructure (10 wt%) and relatively low diffraction intensity of MoS₂ and rGO^{44,45}. X-ray photoelectron spectroscopy (XPS) analyses were performed to investigate the surface elements and chemical states of CZTS/MoS₂-rGO heterostructure. The XPS survey spectrum shown in Fig. S5(a) identified the presence of Cu, Zn, Sn, S, Mo, and C in the CZTS/MoS₂-rGO heterostructure. In the high resolution XPS spectrum of graphene oxide (Fig. S5(b)), C-O and C-C peaks appear with strong intensities and O=C-O peak as a shoulder at 286.2, 284.2, and 288.0 eV, respectively. The CZTS/MoS₂-rGO heterostructure showed a major C 1s signal from C-C at 284.9 eV and a tiny C-O peak at 286.1 eV (Fig. S5(c)). The O=C-O peak has completely disappeared and C-O intensity has significantly decreased, indicating the full reduction of graphene oxide to rGO and reconstruction of π -conjugation in rGO plane during the synthesis of CZTS/MoS₂-rGO heterostructure^{44,46,47}. Two peaks observed at 933.2 and 953.2 eV in the high-resolution XPS spectra were determined to be 2p_{3/2} and 2p_{1/2} states of Cu(I). Zn(II) state was identified from the peak at 1,022.6 eV. The sharp Sn 3d peaks located at 486.9 and 495.4 eV with a peak separation of 8.5 eV confirmed the Sn(IV) state. The sulfur 2p_{3/2} and 2p_{1/2} peaks were identified at 162.4 and 163.4 eV, which agreed with the sulfide phase in the range of 160 and 164 eV. The Mo 3d spectrum showed two peaks at 228.9 and 232 eV which were attributed to the 3d_{3/2} and 3d_{5/2} orbitals, respectively.

In order to further ensure the structural homogeneity, Raman measurements were taken and are shown in Fig. 3. Two peaks at 1,596 and 1,360 cm⁻¹, observed from a pre-synthesized GO, correspond to G and D bands.




Figure 4. Comparison of photocatalytic H₂ evolution from various CZTS/MoS₂-rGO composites with different ratios of MoS₂-rGO co-catalyst. All samples contain 10 wt% co-catalyst incorporated with 90 wt% CZTS. Inset: comparison of photocatalytic H₂ evolution from CZTS/rGO composites of various ratios. Experiment conditions: 1 h irradiation by solar simulator (150 W Xe lamp).

The G band is related to the in-plane vibration mode of sp² carbon, while D band demonstrates defective and partially disordered structures of the carbon to sp³ hybrid carbon. All the characteristic Raman bands for CZTS and few-layer MoS₂ can be found at 335, 383, and 409 cm⁻¹, corresponding to the A_{1g} mode of CZTS and E_{2g}¹, A_{1g} modes of MoS₂, respectively^{43,48,49}. The Raman spectrum of CZTS/MoS₂-rGO heterostructure also reveals the coexistence of all three components with high purity. The heating in oleylamine at high temperature (280 °C) is believed to induce the reduction of graphene oxide to rGO⁴³. The optical properties of heterostructure are also affected by the formation of nanoscale interfacial contact between two different materials. The UV-Vis spectra obtained from CZTS/MoS₂-rGO heterostructure, pristine CZTS nanoparticles, and MoS₂-rGO hybrids are compared in Fig. S6. The pristine CZTS nanoparticle displays a band edge of around 1.3 eV which matches well with the literature value¹⁷. Three distinct peaks observed from MoS₂-rGO at ca. 460, 620, and 665 nm originate from the band gap transition from the valence band to the conduction band of MoS₂⁵⁰. The UV-Vis spectrum of CZTS/MoS₂-rGO heterostructure is similar to that of CZTS, but a small shoulder at ca. 460 nm and a broad peak at 600–850 nm indicate that MoS₂-rGO has been successfully incorporated with CZTS.

Comparative experiments on the photocatalytic H₂ evolution were conducted using CZTS nanoparticle and its heterostructure with MoS₂ and/or rGO. Figure 4 summarizes the results of the H₂ evolution yields from CZTS/MoS₂-rGO heterostructure (5 mg sample size) under 1 h illumination of simulated sunlight. CZTS nanoparticle alone was photocatalytically active, but the rate of H₂ evolution was low (25 μmol g⁻¹ h⁻¹, inset in Fig. 4). We first prepared CZTS/rGO heterostructure with different rGO wt% to study how the presence of rGO affects the rate of H₂ production (inset in Fig. 4). The addition of 2 wt% rGO to CZTS slightly enhanced H₂ generation rate to 37 μmol g⁻¹ h⁻¹. With rGO ratio of 10 wt%, the photocatalytic yield was more than doubled (52 μmol g⁻¹ h⁻¹) which is 106% enhancement. However, further increase of rGO content decreased H₂ production due to the shading effect of rGO that could block the active sites of CZTS²³. Accordingly, we have fixed the amount of hybrid cocatalyst to 10 wt% for the subsequent experiments where both rGO and MoS₂ were engaged. The enhancement effect from the MoS₂-rGO hybrid was much more profound than when rGO or MoS₂ was used as a single component. When 10 wt% MoS₂-rGO hybrid with 95:5 MoS₂:rGO ratio was incorporated into CZTS, the H₂ evolution yield was enhanced by more than 270%. A slight increase of rGO ratio in the MoS₂-rGO hybrid to 90:10 further enhanced the rate of H₂ evolution to 320%. However, the photocatalytic activity of the heterostructure decreased with more than 1 wt% rGO content. Incorporation of 10 wt% MoS₂ as a single component resulted in merely 40% enhancement in H₂ production. In a series of control experiments, the photocatalytic H₂ evolution from GO, MoS₂, MoS₂-rGO hybrid, Au nanoparticle decorated CZTS (Au/CZTS) and Pt nanoparticle decorated CZTS (Pt/CZTS) were also tested for comparison (Figs S7 and S8). All of these systems showed much lower photocatalytic activities than CZTS/MoS₂-rGO heterostructure. Bare MoS₂ and MoS₂-rGO showed low photocatalytic activities for H₂ generation, due to the intrinsic indirect band gap that favors a rapid non-radiative relaxation in the form of phonons (heat) and increases the probability for electron-hole pair recombination^{46,50}. It is worthwhile to note that the H₂ yields from both Au/CZTS and Pt/CZTS are less than half of that from CZTS/MoS₂-rGO heterostructure, demonstrating that a rational design of low-cost nanomaterial heterostructure outperforms the noble metal-loaded semiconductor catalysts. The stability of CZTS/MoS₂-rGO heterostructure was investigated by a prolonged 20 h reaction (Fig. S9). The H₂ yield from CZTS/MoS₂-rGO heterostructure showed a linear correlation with reaction time, indicating its high photocatalytic stabilities under UV-Vis light.

We also carried out a series of electrocatalytic H₂ evolution tests in a typical three-electrode setup using a platinum wire and a saturated calomel electrode (SCE) as the counter and the reference electrode, respectively (Fig. S10). An alkaline solution containing Na₂S (0.35 M) + Na₂SO₃ (0.25 M) was used as the electrolyte in order to maintain the same conditions as in the photocatalytic experiments for comparison. The photocatalyst samples (5 mg) containing various ratios of CZTS, MoS₂, and rGO have been dispersed in Nafion solution and deposited onto a glassy carbon electrode (GCE) by drop-casting. Bare GCE was used as a background reference system. The polarization curve recorded with CZTS-modified GCE showed a poor catalytic activity with the onset of H₂ evolution at -1.62 V. The CZTS (90 wt%)/rGO (10 wt%)-modified GCE exhibited a slight enhancement in




Figure 5. Illustration and energy diagram of interfacial charge transfer and photocatalytic redox reaction in CZTS/MoS₂-rGO composites (the band values are taken from references 20 and 44).

cathodic current and reduction of overpotential. When 10 wt% MoS₂ was used with CZTS instead of rGO, further reduction in the onset potential was observed. MoS₂, which has larger size than CZTS, could also provide efficient electron transfer path, as well as additional active sites for H₂ generation. With both MoS₂ (9 wt%) and rGO (1 wt%) present in the heterostructure, the highest electrocatalytic current density and lowest onset potential were obtained. As suggested by the TEM images (Fig. 1), CZTS, MoS₂, and rGO are in nanoscale contacts with one another and this leads to a much faster electron transfer across the entire heterostructure. The presence of highly conductive rGO carbon network⁵¹ coupled with the superior electrocatalytic activity from the edge of MoS₂ synergistically enhanced the activity of CZTS/MoS₂-rGO heterostructure for electrochemical water reduction^{44,52}. The introduction of MoS₂-rGO hybrid into the CZTS can also increase the number of active sites for both photocatalytic and electrocatalytic H₂ production applications. A proposed photocatalytic H₂ production mechanism is as follows (Fig. 5). Upon the absorption of light, CZTS nanoparticles generate excited electrons and holes. The comparable energy differences among the conduction band of CZTS, Fermi level of rGO, and conduction band of MoS₂ allow the photoexcited electrons to be either directly transferred to the nearby MoS₂ or shuttled across rGO backbone to a remote MoS₂, and consumed for H₂ reduction. It is not yet known how the lifetime of excitons in CZTS is modified in the presence of MoS₂-rGO, but the rapid transfer and isolation of excited electrons from the immobile holes of CZTS to MoS₂ *via* rGO will certainly reduce the radiative recombination of photogenerated electron-hole pairs and prolong the exciton lifetime^{37,46,53,54}. The produced photoelectrons on the edge sulfide sites (both CZTS and MoS₂) are captured by H⁺ and used to reduce H⁺ to H₂, while the holes are consumed by sacrificial agents, S²⁻ and SO₃²⁻, to complete the catalytic cycle.

In conclusion, we have shown the fabrication of CZTS/MoS₂-rGO heterostructure by the wet chemistry approach. The high density of nanoscale interfacial contact between CZTS nanoparticles and MoS₂-rGO hybrid was demonstrated to favor the photogenerated electron transfer from CZTS directly to MoS₂ or through rGO, thus reducing the exciton recombination, increasing the activity sites, and enhancing the photocatalytic efficiency for H₂ generation. The MoS₂-rGO hybrid has shown a synergistic effect when combined with CZTS, which makes this heterostructure an excellent H₂ evolution photocatalytic system with a long-term durability.

Methods

Synthesis of graphene oxide. Graphene oxide (GO) was synthesized by an improved Hummers' method⁵⁵. Typically, a mixture of concentrated H₂SO₄ (120 mL) and H₃PO₄ (13.3 mL) was slowly added to a mixture of graphite flakes (1 g) and KMnO₄ (6 g), and then heated to 50 °C and stirred for 12 h. After the reaction, the reaction mixture was cooled down to room temperature and poured onto ice (400 mL) with 30% H₂O₂ (3 mL). After another 1 h stirring, the mixture was centrifuged at 4,000 rpm for 4 h, and the supernatant was decanted away. The remaining solid material was then washed sequentially with water (200 mL), 37% HCl (200 mL), and ethanol (200 mL). Finally, it was purified by dialysis over one week using a dialysis membrane (Promega SV Minicolumns). The solid obtained was vacuum-dried at 60 °C and the yield is 585 mg.

Synthesis of MoS₂. In a typical synthesis of few-layer MoS₂⁴⁴, 242 mg Na₂MoO₄·2H₂O and 380 mg CS(NH₂)₂ were dissolved in 60 mL distilled water. The homogeneous solution was then transferred into a 100 mL Teflon-lined autoclave and held at 210 °C for 24 h. After the completion of reaction, the black precipitate was collected by centrifugation, washed three times with distilled water and ethanol, and then dried in a vacuum oven at 60 °C. The yield of MoS₂ is 167 mg.

Synthesis of Cu₂ZnSnS₄. CZTS nanoparticles were synthesized by an optimized method described by Chet Steinhagen *et al.*¹⁷. In a typical procedure, 260 mg Cu(acac)₂, 145 mg Zn(OAc)₂, 112 mg SnCl₂·2H₂O, and 15 mL oleylamine were mixed in a three-necked flask at room temperature. After 2 h under vacuum, water and low boiling point solvents in oleylamine were removed by bubbling with N₂ for 30 min at 120 °C. 65 mg of elemental sulfur

was dissolved in 5 mL oleylamine by sonicating for 30 min and then injected into the reaction flask containing metal-oleylamine precursors, and the temperature was raised to 280 °C. After 1 h reaction, the resulting product was cooled down to room temperature. Upon the addition of absolute ethanol, the reaction was quenched and the nanoparticles precipitated out. The obtained nanoparticles were washed three times with ethanol and chloroform in turns. The yield of resulting CZTS nanoparticles is around 180 mg.

Synthesis of heterostructure. MoS₂-rGO heterostructure was synthesized by dispersing different amount of GO in the synthesis of MoS₂⁴⁴. The CZTS/MoS₂, CZTS/rGO, and CZTS/MoS₂-rGO heterostructure were prepared by dispersing MoS₂, rGO, and MoS₂-rGO with different weight ratio into the sulfur-oleylamine solution, respectively, and injecting it to the metal-oleylamine solution for the growth of CZTS nanoparticles. Platinum nanoparticle decorated CZTS (Pt/CZTS) photocatalyst was prepared by photodeposition method. H₂PtCl₆·6H₂O (10.62 mg) and CZTS (40 mg) were dispersed in 30 mL ethanol by sonication for 1 h and irradiated with 150 W Xe lamp for 30 min. Gold nanoparticle decorated CZTS (Au/CZTS) photocatalyst was prepared by dispersing 6 mg HAuCl₄·3H₂O in 5 mL oleylamine at 60 °C. 30 mg of freshly prepared CZTS was dispersed in 3 mL CHCl₃, which was swiftly injected into the Au-oleylamine precursor solution and the temperature was raised to 90 °C for 10 min.

Characterization and Measurement. X-ray diffraction spectrum was taken using a SmartLab[®] X-ray diffractometer (Rigaku) with a diffraction angle 2θ ranging from 10 to 90°. Transmission electron microscopic (TEM) images were obtained using a STEM (JEOL JEM-2100F) operated at 200 kV. The samples were first dispersed in CHCl₃ by sonication and drop-cast onto holey carbon-coated 400 mesh nickel TEM grids. The elemental compositions of these materials were characterized by an energy dispersive spectrometer (EDS) attached to the STEM. Raman microprobe measurements were performed by a Raman spectrometer (LabRam HR800-UV, Horiba-Jobin Yvon) with excitation wavelength of 532 nm at room temperature. UV-Vis absorption spectra were recorded on a Hewlett Packard Model 8453 Diode Array UV-Vis Spectrophotometer. The sample solutions were prepared in chloroform using a quartz cuvette of 1 cm path length. XPS was performed on an ESCALAB 250Xi ultrahigh vacuum (UHV) surface analysis system (Thermo Fisher Scientific) with a monochromic Al K_α X-ray source (1486.6 eV). A thin film was formed by drop-casting the sample solution on single crystal silicon substrate for measurement. Electrochemical measurements were performed using a 1030 A CHI electrochemical station. 5 mg of catalyst and 100 μL of 5 wt% Nafion solution were dispersed in 2 mL of 4:1 v/v water/ethanol by 10 min sonication to form homogeneous suspension. Then, 5 μL of the catalyst ink was drop-cast onto a glassy carbon electrode of 3 mm diameter (surface area: 0.07 cm²). A linear sweep voltammogram from 0 to -1.8 V was conducted at a scan rate of 2 mV s⁻¹ in a Na₂S (0.35 M) + Na₂SO₃ (0.25 M) solution using a saturated calomel electrode as the reference electrode, a Pt wire as the counter electrode, and a glassy carbon electrode as the working electrode. For photocatalytic hydrogen evolution experiments, catalyst in ca. 5 mg was dispersed in an aqueous solution containing 25 mL Na₂S (0.35 M) + Na₂SO₃ (0.25 M), and irradiated with a Newport solar simulator (150 W Xe lamp, ozone free, Air Mass Filter, AM 1.5 Global) of 70 mW cm⁻² light intensity for 1 h. The amount of generated hydrogen was analyzed by an Agilent 7890B gas chromatograph system equipped with a TCD detector using N₂ as carrier gas.

References

- Chen, X., Shen, S., Guo, L. & Mao, S. S. Semiconductor-based Photocatalytic Hydrogen Generation. *Chem. Rev.* **110**, 6503–6570 (2010).
- Marschall, R. Semiconductor Composites: Strategies for Enhancing Charge Carrier Separation to Improve Photocatalytic Activity. *Adv. Funct. Mater.* **24**, 2421–2440 (2013).
- Han, B., Wei, W., Chang, L., Cheng, P. & Hu, Y. H. Efficient Visible Light Photocatalytic CO₂ Reforming of CH₄. *ACS Catal.* **6**, 494–497 (2016).
- Han, B. & Hu, Y. H. Highly Efficient Temperature-Induced Visible Light Photocatalytic Hydrogen Production from Water. *J. Phys. Chem. C* **119**, 18927–18934 (2015).
- Talapin, D. V., Lee, J.-S., Kovalenko, M. V. & Shevchenko, E. V. Prospects of Colloidal Nanocrystals for Electronic and Optoelectronic Applications. *Chem. Rev.* **110**, 389–458 (2009).
- Hillhouse, H. W. & Beard, M. C. Solar cells from colloidal nanocrystals: Fundamentals, materials, devices, and economics. *Curr. Opin. Colloid Interface Sci.* **14**, 245–259 (2009).
- Shirasaki, Y., Supran, G. J., Bawendi, M. G. & Bulovic, V. Emergence of colloidal quantum-dot light-emitting technologies. *Nat. Photon* **7**, 13–23 (2013).
- Fujishima, A. & Honda, K. Electrochemical photolysis of water at a semiconductor electrode. *Nature* **238**, 37–38 (1972).
- Cesar, I., Sivula, K., Kay, A., Zboril, R. & Grätzel, M. Influence of Feature Size, Film Thickness, and Silicon Doping on the Performance of Nanostructured Hematite Photoanodes for Solar Water Splitting. *J. Phys. Chem. C* **113**, 772–782 (2008).
- Hussein, A. M. *et al.* Mesoporous coupled ZnO/TiO₂ photocatalyst nanocomposites for hydrogen generation. *J. Renew. Sustain. Ener.* **5**, 033118 (2013).
- Hu, Y. H. A Highly Efficient Photocatalyst—Hydrogenated Black TiO₂ for the Photocatalytic Splitting of Water. *Angew. Chem. Int. Ed.* **51**, 12410–12412 (2012).
- Zhang, K. *et al.* An order/disorder/water junction system for highly efficient co-catalyst-free photocatalytic hydrogen generation. *Energy Environ. Sci.* **9**, 499–503 (2016).
- Bao, N., Shen, L., Takata, T. & Domen, K. Self-Templated Synthesis of Nanoporous CdS Nanostructures for Highly Efficient Photocatalytic Hydrogen Production under Visible Light. *Chem. Mater.* **20**, 110–117 (2007).
- Zhang, K. & Guo, L. Metal sulphide semiconductors for photocatalytic hydrogen production. *Catal. Sci. Technol.* **3**, 1672–1690 (2013).
- Tabata, M. *et al.* Photocatalytic Hydrogen Evolution from Water Using Copper Gallium Sulfide under Visible-Light Irradiation. *J. Phys. Chem. C* **114**, 11215–11220 (2010).
- Guo, Q., Hillhouse, H. W. & Agrawal, R. Synthesis of Cu₂ZnSnS₄ Nanocrystal Ink and Its Use for Solar Cells. *J. Am. Chem. Soc.* **131**, 11672–11673 (2009).
- Steinhagen, C. *et al.* Synthesis of Cu₂ZnSnS₄ Nanocrystals for Use in Low-Cost Photovoltaics. *J. Am. Chem. Soc.* **131**, 12554–12555 (2009).

18. Singh, A., Geaney, H., Laffir, F. & Ryan, K. M. Colloidal Synthesis of Wurtzite $\text{Cu}_2\text{ZnSnS}_4$ Nanorods and Their Perpendicular Assembly. *J. Am. Chem. Soc.* **134**, 2910–2913 (2012).
19. Wang, L., Wang, W. & Sun, S. A simple template-free synthesis of ultrathin $\text{Cu}_2\text{ZnSnS}_4$ nanosheets for highly stable photocatalytic H_2 evolution. *J. Mater. Chem.* **22**, 6553–6555 (2012).
20. Ha, E. *et al.* Significant Enhancement in Photocatalytic Reduction of Water to Hydrogen by Au/ $\text{Cu}_2\text{ZnSnS}_4$ Nanostructure. *Adv. Mater.* **26**, 3496–3500 (2014).
21. Ha, E., Lee, L. Y. S., Man, H.-W., Tsang, S. C. E. & Wong, K.-Y. Morphology-Controlled Synthesis of Au/ $\text{Cu}_2\text{FeSnS}_4$ Core–Shell Nanostructures for Plasmon-Enhanced Photocatalytic Hydrogen Generation. *Appl. Mater. Interfaces* **7**, 9072–9077 (2015).
22. Yu, X. *et al.* $\text{Cu}_2\text{ZnSnS}_4$ -Pt and $\text{Cu}_2\text{ZnSnS}_4$ -Au Heterostructured Nanoparticles for Photocatalytic Water Splitting and Pollutant Degradation. *J. Am. Chem. Soc.* **136**, 9236–9239 (2014).
23. Yang, W. *et al.* Interfacial charge transfer and enhanced photocatalytic performance for the heterojunction WO_3/BiOCl : first-principles study. *J. Mater. Chem. A* **2**, 20770–20775 (2014).
24. Niu, M. *et al.* Hydrothermal Synthesis, Structural Characteristics, and Enhanced Photocatalysis of $\text{SnO}_2/\alpha\text{-Fe}_2\text{O}_3$ Semiconductor Nanoheterostructures. *ACS Nano* **4**, 681–688 (2010).
25. Dutta, S. K., Mehetor, S. K. & Pradhan, N. Metal Semiconductor Heterostructures for Photocatalytic Conversion of Light Energy. *J. Phys. Chem. Lett.* **6**, 936–944 (2015).
26. Li, L., Salvador, P. A. & Rohrer, G. S. Photocatalysts with internal electric fields. *Nanoscale* **6**, 24–42 (2014).
27. Zhang, C. *et al.* *In situ* fabrication of $\text{Bi}_2\text{WO}_6/\text{MoS}_2/\text{RGO}$ heterojunction with nanosized interfacial contact via confined space effect towards enhanced photocatalytic properties. *ACS Sustain. Chem. & Eng.* doi: 10.1021/acssuschemeng.6b00640 (2016).
28. Zhang, Z.-c., Xu, B. & Wang, X. Engineering nanointerfaces for nanocatalysis. *Chem. Soc. Rev.* **43**, 7870–7886 (2014).
29. Tan, C. & Zhang, H. Epitaxial Growth of Hetero-Nanostructures Based on Ultrathin Two-Dimensional Nanosheets. *J. Am. Chem. Soc.* **137**, 12162–12174 (2015).
30. Xu, L. *et al.* Synchronous etching-epitaxial growth fabrication of facet-coupling $\text{NaTaO}_3/\text{Ta}_2\text{O}_5$ heterostructured nanofibers for enhanced photocatalytic hydrogen production. *Appl. Catal., B* **184**, 309–319 (2016).
31. Xu, B. *et al.* A 1D/2D Helical $\text{CdS}/\text{ZnIn}_2\text{S}_4$ Nano-Heterostructure. *Angew. Chem. Int. Ed.* **53**, 2339–2343 (2014).
32. Novoselov, K. S. *et al.* A roadmap for graphene. *Nature* **490**, 192–200 (2012).
33. Hu, Y. H., Wang, H. & Hu, B. Thinnest Two-Dimensional Nanomaterial—Graphene for Solar Energy. *ChemSusChem* **3**, 782–796 (2010).
34. Du, X., Skachko, I., Barker, A. & Andrei, E. Y. Approaching ballistic transport in suspended graphene. *Nat. Nano* **3**, 491–495 (2008).
35. Han, B. & Hu, Y. H. MoS_2 as a co-catalyst for photocatalytic hydrogen production from water. *Energy Sci. & Eng.* doi: 10.1002/ese3.128 (2016).
36. Jaramillo, T. F. *et al.* Identification of Active Edge Sites for Electrochemical H_2 Evolution from MoS_2 Nanocatalysts. *Science* **317**, 100–102 (2007).
37. Zhang, K. *et al.* Delocalized Electron Accumulation at Nanorod Tips: Origin of Efficient H_2 Generation. *Adv. Funct. Mater.* **26**, 4527–4534 (2016).
38. Li, H. *et al.* Few-layered MoS_2 nanosheets wrapped ultrafine TiO_2 nanobelts with enhanced photocatalytic property. *Nanoscale* **8**, 6101–6109 (2016).
39. Tran, P. D. *et al.* A cuprous oxide-reduced graphene oxide (Cu_2O -rGO) composite photocatalyst for hydrogen generation: employing rGO as an electron acceptor to enhance the photocatalytic activity and stability of Cu_2O . *Nanoscale* **4**, 3875–3878 (2012).
40. Yu, X. *et al.* Hierarchical hybrid nanostructures of Sn_3O_4 on N doped TiO_2 nanotubes with enhanced photocatalytic performance. *J. Mater. Chem. A* **3**, 19129–19136 (2015).
41. Thomson, J. W., Nagashima, K., Macdonald, P. M. & Ozin, G. A. From Sulfur–Amine Solutions to Metal Sulfide Nanocrystals: Peering into the Oleylamine–Sulfur Black Box. *J. Am. Chem. Soc.* **133**, 5036–5041 (2011).
42. Borisova, D., Antonov, V. & Proykova, A. Hydrogen sulfide adsorption on a defective graphene. *Int. J. Quantum Chem.* **113**, 786–791 (2013).
43. Thangaraju, D., Karthikeyan, R., Prakash, N., Moorthy Babu, S. & Hayakawa, Y. Growth and optical properties of $\text{Cu}_2\text{ZnSnS}_4$ decorated reduced graphene oxide nanocomposites. *Dalton Trans.* **44**, 15031–15041 (2015).
44. Xiang, Q., Yu, J. & Jaroniec, M. Synergetic Effect of MoS_2 and Graphene as Cocatalysts for Enhanced Photocatalytic H_2 Production Activity of TiO_2 Nanoparticles. *J. Am. Chem. Soc.* **134**, 6575–6578 (2012).
45. Zhu, B. *et al.* Enhanced photocatalytic H_2 evolution on ZnS loaded with graphene and MoS_2 nanosheets as cocatalysts. *J. Mater. Chem. A* **2**, 3819–3827 (2014).
46. Jia, T. *et al.* A graphene dispersed CdS - MoS_2 nanocrystal ensemble for cooperative photocatalytic hydrogen production from water. *Chem. Comm.* **50**, 1185–1188 (2014).
47. Wang, L. *et al.* Dual n-type doped reduced graphene oxide field effect transistors controlled by semiconductor nanocrystals. *Chem. Comm.* **48**, 4052–4054 (2012).
48. Li, Y. *et al.* MoS_2 Nanoparticles Grown on Graphene: An Advanced Catalyst for the Hydrogen Evolution Reaction. *J. Am. Chem. Soc.* **133**, 7296–7299 (2011).
49. Liu, C.-J. *et al.* Facile synthesis of MoS_2 /graphene nanocomposite with high catalytic activity toward triiodide reduction in dye-sensitized solar cells. *J. Mater. Chem.* **22**, 21057–21064 (2012).
50. Mak, K. F., Lee, C., Hone, J., Shan, J. & Heinz, T. F. Atomically Thin MoS_2 : A New Direct-Gap Semiconductor. *Phys. Rev. Lett.* **105**, 136805 (2010).
51. Geim, A. K. & Novoselov, K. S. The rise of graphene. *Nat Mater* **6**, 183–191 (2007).
52. Zong, X. *et al.* Enhancement of Photocatalytic H_2 Evolution on CdS by Loading MoS_2 as Cocatalyst under Visible Light Irradiation. *J. Am. Chem. Soc.* **130**, 7176–7177 (2008).
53. Jahurul Islam, M. *et al.* An oxygen-vacancy rich 3D novel hierarchical $\text{MoS}_2/\text{BiOI}/\text{AgI}$ ternary nanocomposite: enhanced photocatalytic activity through photogenerated electron shuttling in a Z-scheme manner. *Phys. Chem. Chem. Phys.* **18**, 24984–24993 (2016).
54. Tian, B., Li, Z., Zhen, W. & Lu, G. Uniformly Sized (112) Facet Co_3P on Graphene for Highly Effective Photocatalytic Hydrogen Evolution. *J. Phys. Chem. C* **120**, 6409–6415 (2016).
55. Marcano, D. C. *et al.* Improved Synthesis of Graphene Oxide. *ACS Nano* **4**, 4806–4814 (2010).

Acknowledgements

We acknowledge the support from the Innovation and Technology Commission and the Hong Kong Polytechnic University. K.Y.W. acknowledges the support from the Patrick S.C. Poon Endowed Professorship.

Author Contributions

K.Y.W. and L.Y.S.L. proposed the idea and supervised the study. E.H. designed the experiments and analyzed the data. W.L. performed the experiment and characterization. L.W. helped with the graphene oxide synthesis. H.W.M. helped with the GC characterization. L.H. helped with the XPS analysis. C.T.L.C. and W.M.K. carried

out PL measurements. S.C.E.T. helped the design of experiment and interpreted mechanism. E.H. and L.Y.S.L. wrote the main manuscript text. All the authors contributed to data analysis and discussion for the manuscript.

Additional Information

Supplementary information accompanies this paper at <http://www.nature.com/srep>

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: Ha, E. *et al.* Cu₂ZnSnS₄/MoS₂-Reduced Graphene Oxide Heterostructure: Nanoscale Interfacial Contact and Enhanced Photocatalytic Hydrogen Generation. *Sci. Rep.* **7**, 39411; doi: 10.1038/srep39411 (2017).

Publisher's note: Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.



This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>

© The Author(s) 2017