

SCIENTIFIC REPORTS

OPEN

Characterization of the second- and third-harmonic optical susceptibilities of atomically thin tungsten diselenide

Henrique G. Rosa¹, Yi Wei Ho^{1,2,3}, Ivan Verzhbitskiy^{1,3}, Manuel J. F. L. Rodrigues^{1,4}, Takashi Taniguchi⁵, Kenji Watanabe⁵, Goki Eda^{1,3,6}, Vitor M. Pereira^{1,3} & José C. V. Gomes^{1,3}

We report the first detailed characterization of the sheet third-harmonic optical susceptibility, $\chi^{(3)}_{sr}$, of tungsten diselenide (WSe_2). With a home-built multiphoton microscope setup developed to study harmonics generation, we map the second and third-harmonic intensities as a function of position in the sample, pump power and polarization angle, for single- and few-layers flakes of WSe_2 . We register a value of $|\chi^{(3)}_{sr}| \approx 0.9 \times 10^{-28} \text{ m}^3 \text{ V}^{-2}$ at a fundamental excitation frequency of $\hbar\omega = 0.8 \text{ eV}$, which is comparable in magnitude to the third-harmonic susceptibility of other group-VI transition metal dichalcogenides. The simultaneously recorded sheet second-harmonic susceptibility is found to be $|\chi^{(2)}_{sr}| \approx 0.7 \times 10^{-19} \text{ m}^2 \text{ V}^{-1}$ in very good agreement on the order of magnitude with recent reports for WSe_2 , which asserts the robustness of our values for $|\chi^{(3)}_{sr}|$.

Atomically thin two-dimensional crystals of semiconducting transition-metal dichalcogenides (TMD) are currently a subject of intense research. The most prominent members of this family have been molybdenum disulfide (MoS_2) and diselenide ($MoSe_2$), as well as tungsten disulfide (WS_2) and diselenide (WSe_2). Their unique electronic, optical and structural characteristics are under active scrutiny for applications in photonics, optoelectronics and electronic devices. In addition to the ability of tuning their carrier densities on demand by field-effect, such properties include high charge-carrier mobility^{1,2}, a direct band gap in monolayer crystals that evolves to indirect with additional layers³, photoluminescent emission in the visible-NIR spectral range⁴⁻⁶, high nonlinear optical susceptibilities^{7,8}, strong spin-orbit coupling^{9,10} and spin-valley locking and novel valleytronics phenomena¹¹.

Owing to their semiconducting character and favorable band gaps for conventional optoelectronics¹², the pressing need for detailed characterization of their intrinsic optical response has stimulated a steady and broad array of experimental results^{12,13}. In particular, nonlinear optical applications hinge upon the nature of the second and third-order optical susceptibilities ($\chi^{(2)}$ and $\chi^{(3)}$, respectively), which are conventionally obtained from harmonic generation experiments. Whereas second-harmonic generation (SHG) in the most prominent TMD had been studied in a number of recent experiments^{7,8,14-16}, reports on third-harmonic generation (THG) among this family have been scarce^{17,18}. Remarkably, THG in either single or few-layer selenide-TMD remains unexplored. These results on harmonic generation in TMD and in other 2D layered materials have been summarized in a recent review by Autere *et al.*^{19,20}.

In this context, we have used multiphoton spectroscopy to simultaneously measure SHG and THG intensities of exfoliated single- and few-layers WSe_2 . By studying the harmonics generation as a function of pump power, layer-dependence and spatial position, and correlating the data with atomic force microscopy, we are able to

¹Centre for Advanced 2D Materials (CA2DM), National University of Singapore, 6 Science Drive 2, Singapore, 117546, Singapore. ²NUS Graduate School for Integrative Sciences and Engineering (NGS), Centre for Life Sciences (CeLS), 28 Medical Drive, Singapore, 117456, Singapore. ³Department of Physics, National University of Singapore, 2 Science Drive 3, Singapore, 117551, Singapore. ⁴Center of Physics and Department of Physics, Universidade do Minho, 4710-057, Braga, Portugal. ⁵National Institute for Materials Science, 1-1 Namiki, Tsukuba, 305-0044, Japan. ⁶Department of Chemistry, National University of Singapore, 3 Science Drive 3, Singapore, 117543, Singapore. Henrique G. Rosa and Yi Wei Ho contributed equally to this work. Correspondence and requests for materials should be addressed to V.M.P. (email: vpereira@nus.edu.sg) or J.C.V.G. (email: phyjvc@nus.edu.sg)




Figure 1. Spectra for (a) 1550 nm pump, (b) SHG at $\lambda_{\text{central}} = 773$ nm and (c) THG at $\lambda_{\text{central}} = 516$ nm. The pump beam full-width at half-maximum (FWHM) bandwidth is 25.1 nm, but only the peak centered at 1546 nm contributes for the harmonic generation (dotted line, FWHM bandwidth ~ 16.3 nm). The FWHM bandwidth and central wavelength for SHG are 8.1 nm and 773 nm, and for THG are 5.8 nm and 516 nm, respectively.

report a robust characterization of third-harmonic $\chi^{(3)}$. We demonstrate that THG is independent on the polarization angle and is proportional to the square of the number of layers. We further show that the magnitude of WSe_2 $\chi^{(3)}$ is comparable to that of sulfides of the same TMD family. Even though this type of experiment has been broadly applied to determine $\chi^{(2)}$ and $\chi^{(3)}$ in several two-dimensional materials^{14,18,21}, the characterization of THG and a quantitative measurement of $\chi^{(3)}$ in WSe_2 had remained unknown.

Results and Discussion

We investigated the nonlinear optical properties of mechanically exfoliated atomically thin 2H- WSe_2 (2H polytype) with a home-built multiphoton microscope specifically designed for harmonics generation. Before nonlinear optical experiments, the sample was extensively characterized by photoluminescence and Raman spectroscopy, as well as by atomic force microscopy (for details on the sample preparation, characterization and experimental setup, see materials and methods section and supporting information). The pump wavelength for the harmonic experiments is 1546 nm, therefore SHG emission is centered at 773 nm and THG emission at 516 nm, as shown in Fig. 1.

The absolute orientation of the WSe_2 crystal, relatively to the laboratory frame, was determined by polarized second-harmonic generation (pSHG), where the incident pump linear polarization and a parallel polarizer were rotated simultaneously by the same angle θ while recording the spectrum. Since 2H- WSe_2 belongs to the D_{3h} point group²², as expected from the threefold rotational symmetry along the c crystallographic axis and demonstrated for a number of odd-layered TMD of this family, the pSHG intensity is proportional to $\cos^2[3(\theta - \phi_0)]$, where ϕ_0 is the angle of the armchair direction of the flake in the laboratory frame. The result of our pSHG is shown in Fig. 2a. This strong polarization dependence makes pSHG a preferred tool for fast crystallographic alignment of these materials^{7,8,14,23}. In contrast, the THG is polarization independent, as can be seen from Fig. 2b, as expected for all other crystals belonging to the D_{3h} group¹⁸. Figure 2c shows an optical image of the sample with the identification of armchair (AC) and zig-zag (ZZ) directions of the flakes⁸.

We hence determined the AC direction to lie at $\phi_0 = -4.4^\circ + m \times 60^\circ$, $m \in \mathbb{Z}$, and set the pump polarization parallel to this direction of maximum response for our subsequent SHG and THG experiments.

To assert the second and third-harmonic nature of the signals discussed so far, we measured their dependence on the pump power via Malus' law experiment, by inserting a fixed polarizer before the sample in the experimental setup used for pSHG measurements (for more details on the experimental setup, see supporting information). Additionally, we carried out a calibration leading to actual average power readings from spectrometer counts in order to extract the magnitude of the susceptibilities (for more details on calibration factors, see supporting information). Figure 3 shows power-dependent double logarithmic plots of SHG and THG actual average power. The power scaling of the SHG and THG intensities is shown to follow very well the respectively expected quadratic and cubic dependences.

To acquire spatial maps, the sample was raster scanned across the pump beam in 0.5 μm steps, while SHG and THG intensities were recorded simultaneously. The results are shown in Fig. 4. An image of the sample with the number of layers (N) labeled in each region, is shown in Fig. 4a. The thickness assignment was performed by correlating atomic force microscopy data with the SHG contrast. The image also shows the presence of a thin film of hexagonal boron nitride (hBN) partially covering the WSe_2 multilayer, which was used to prevent environmental degradation (for more details on sample fabrication, see supporting information).

Figure 4b shows the sharp SHG contrast between regions of odd- and even- N , as SHG in these TMD is expected for odd- N flakes^{24,25}, with a decreasing intensity for increasing number of layers^{10,26}. Yet, even though SHG is expected to be strictly zero for even- N , a residual non-zero intensity is recorded for 4- and 6-layers regions, as shown in Fig. 4d. This effect might be attributed to incomplete destructive interference between SHG from adjacent layers, as discussed previously by Li *et al.*²⁵, although its fundamental cause remains unexplored. Moreover, this effect might be responsible for a small negative slope for the SHG intensity as a function of the odd- N . Extrapolating the linearly decreasing trend inferred from Fig. 4d, significant SHG intensity in WSe_2




Figure 2. Polarized harmonic generation in WSe_2 : (a) SHG, $\phi_0 = -4.4^\circ$ and (b) THG, constant intensity with θ ; (c) optical image of the sample with armchair (AC) and zig-zag (ZZ) directions.




Figure 3. Double logarithmic plots of the power-dependent nonlinear signals for (a) the SHG of single-layer and (b) the THG of 9-layers WSe_2 .

should be observed for samples with up to ~ 50 layers. However, the challenges in unambiguously determining N for samples with more than 10 layers make this observation difficult.

Figure 4c shows the THG map of the sample. In addition to the signal now arising from all regions of the sample, the key observation is that the intensity clearly scales up with the number of layers. To be more specific and quantitative, we compiled the average intensity over regions with same N in Fig. 4c. The THG intensity is proportional to N^2 , as shown in Fig. 4e. This quadratic scaling with thickness is a direct evidence that we can consider each layer as contributing independently to the overall THG, since the linear relation of the third-harmonic susceptibility $|\chi^{(3)}_N| = N \times |\chi^{(3)}_s|$ indeed implies $I_{\text{THG}} \propto |\chi^{(3)}_N|^2 \propto N^2 \times |\chi^{(3)}_s|^2$.

No border effect for enhancement of SHG or THG was observed. In fact, DFT calculations for chemical vapour deposited (CVD) WS₂ showed that at the borders the bandgap becomes indirect^{27,28}, which actually contributes to quenching of SHG and, probably, THG at the edges.

A direct comparison between Fig. 4a and c indicates that regions with same N have slightly weaker harmonic intensities when covered by hBN, which the most notable case being the 5-layers region. This can be explained by the Fresnel reflection/transmission coefficients, since the total transmittance depends on the layer stacking, total sample thickness and refractive index mismatch. We observed that, by recording the transmitted power at the fundamental frequency with a reference photodetector, regions without hBN may have up to 4% higher pump transmittance than covered regions (for more details on reference transmittance mapping, see supporting information). This difference in pump power leads to SHG and THG intensities of, respectively, 8% and 12% higher in non-covered regions. The analysis presented in Fig. 4d and e already corrects the intensities by the pump power in each region. The contribution to SHG and THG from hBN solely is negligible, as we have confirmed by pumping hBN regions of the sample (Fig. 4b and c). This agrees with previous report by Li *et al.*²⁵, where the authors show that hBN $|\chi^{(2)}_s|$ is 2 orders of magnitude lower than that of TMD.




Figure 4. (a) Optical image of the sample with labeled number of layers (N); (b) Spatial SHG and (c) THG intensity mappings across the WSe_2 sample; (d) Spatial average SHG and (e) THG intensities as a function of N . The values and error bars indicated for the SHG and THG correspond to the mean $\pm 3 \times$ (standard deviation). Scale bars = 10 μm .

Taking advantage of the spatial resolution and well defined layer assignment in our experiment, the magnitude of the nonlinear susceptibilities $\chi^{(2)}$ and $\chi^{(3)}$ for WSe_2 were extracted from the harmonic mapping by using the model deduced by Woodward *et al.*¹⁸. Simple modifications were implemented in the model, accounting for harmonic generation in transmittance, with fundamental beam pumping the sample from the substrate-sample interface, as shown in Equation (1) and (2):

$$|\chi_s^{(2)}| = \sqrt{\frac{P(2\omega)}{P^2(\omega)} \times \frac{c \cdot \epsilon_0 \cdot RR \cdot A \cdot \Delta\tau \cdot \lambda^2}{64\sqrt{2}\pi^2 S} \times \frac{(1+n)^6}{n^3}}, \quad (1)$$

$$|\chi_s^{(3)}| = \sqrt{\frac{P(3\omega)}{P^3(\omega)} \times \frac{c^2 \cdot \epsilon_0^2 \cdot RR^2 \cdot A^2 \cdot \Delta\tau^2 \cdot \lambda^2}{336\sqrt{3}\pi^2 S^2} \times \frac{(1+n)^8}{n^4}}, \quad (2)$$

where $P(2\omega)$ and $P(3\omega)$ are second-harmonic and third-harmonic average powers, respectively, and $P(\omega)$ is the fundamental average power. c is the speed of light in vacuum, ϵ_0 is the vacuum electric permittivity. RR is the repetition rate (80 MHz), A is the minimum spot area ($2.0 \pm 0.3 \mu\text{m}^2$, obtained from the half-width at $1/e^2$ beam radius of $0.8 \pm 0.1 \mu\text{m}$), $\Delta\tau$ is the full-width at half maximum pulse duration at the sample spot (200 ± 10 fs) and λ is the wavelength (1545 nm) for the fundamental beam. Finally, n is the substrate refractive index at the fundamental wavelength (1.47 at 1545 nm) and $S = 0.94$ is a shape factor assuming Gaussian pulses. The average power of the fundamental beam was kept constant at 0.65 mW, and the calibration factors to obtain harmonic average powers from counts, as in Fig. 4, are 0.275 fW counts⁻¹ and 0.512 fW counts⁻¹, respectively, for SHG and THG. $|\chi_s^{(2)}|$ and $|\chi_s^{(3)}|$ results are summarized in Table 1.

As only odd- N regions contribute with appreciable SHG, the second-order susceptibility is expressed in terms of an effective value $|\chi_s^{(2)}|$, which was directly obtained from each region on the WSe_2 sample. The third-order susceptibility is expressed in terms of both an effective value, $|\chi_s^{(3)}|$, and the average per layer, $|\chi^{(3)}|$. The bulk-like values are obtained from the expression $|\chi_b| = |\chi_s|/\delta$, where δ is the inter-layer distance of the flake (for our WSe_2 flake, $\delta = 0.79 \pm 0.02$ nm – for more details on the thickness characterization, see supporting information).

The values obtained for sheet and bulk second-order susceptibility agree with those previously reported^{7,29} within the order of magnitude, and the sheet and bulk values of third-harmonic susceptibility are reported here for the first time. The $\chi^{(3)}$ magnitude is comparable to other TMD^{18,30} and is larger than that reported for graphene^{18,31}. Although the presented results have small errors inherent from the model and parameters we used ($\sim 13\%$ for SHG at odd- N , $\sim 13\%$ for THG – except $N = 1$ with 20% error), those should only be taken as a good estimative for the order of magnitude of such susceptibilities, since their determination relies on the precise measurement of many important parameters (which can vary upon definitions and measurement techniques). The measurement of harmonic susceptibilities of two-dimensional layered materials is known to be sensitive to the fabrication process (Woodward *et al.*¹⁸ reported 26% variation between exfoliated and CVD MoS_2), stacking order, and surrounding environment (substrate and superstrate)¹⁹.

Number of layers (N)	$ \chi^{(2)}_N $ ($10^{-19} \text{ m}^2 \text{ V}^{-1}$)	$ \chi^{(3)}_N $ ($10^{-28} \text{ m}^3 \text{ V}^{-2}$)
1	0.70 ± 0.09	0.9 ± 0.2
4	0.08 ± 0.08	3.4 ± 0.5
5	0.67 ± 0.09	4.5 ± 0.6
6	0.2 ± 0.1	6.0 ± 0.8
9	0.65 ± 0.08	8.6 ± 0.9
Average/sheet (per layer)	—	0.91 ± 0.07
	$ \chi^{(2)}_b $ ($10^{-10} \text{ m V}^{-1}$)	$ \chi^{(3)}_b $ ($10^{-19} \text{ m}^2 \text{ V}^{-2}$)
Bulk susceptibility	0.9 ± 0.1	1.16 ± 0.09

Table 1. Harmonic susceptibilities of WSe₂ as a function of number of layers N . The reported values correspond to the mean \pm standard deviation. The error values are obtained from the uncertainties of the relevant experimental parameters present in equations (1) and (2), through classical error propagation theory.

Excitons are strongly present in semiconductor TMD, excitonic effects may also play role by enhancing non-linear optical transitions, as reported previously for MoS₂⁸ and for WSe₂^{32,33}: when the harmonic photon energies are in resonances to excitonic or single-particle energy levels from the material, harmonic signals up to 1 order of magnitude higher might be observed. Since in our experiment WSe₂ is pumped by photons of 0.8 eV, no resonant enhancement effect is expected to take place, because both SHG (1.6 eV) and THG (2.4 eV) are off-resonance with energy levels of the material³⁴. Nevertheless, our SHG results agrees to those off-resonance published results. Although no resonance has been observed, the presented characterization provides important parameters to support the realization of 2D-materials-based devices for applications in telecommunication systems and silicon photonics.

Benefiting from the small sample thickness and THG efficiency, multi-layer WSe₂ appears to be a potential material for nonlinear optical applications as, for example, on-chip optical frequency conversion³⁵, silicon photonics^{36,37}, or other third-order related phenomena like all-optical switching^{38,39}, which depends on a different $\chi^{(3)}$.

Conclusion

By extensively characterizing single- and few-layers flakes of 2H-WSe₂ with photoluminescence, Raman spectroscopy and atomic force microscopy, we obtained the precise number of layers of each regions of the flake. We mapped the spatial emission of the second- and third-harmonic signals to study the layer dependence of the non-linear response and quantified the corresponding susceptibilities. We obtained the values $|\chi^{(3)}_s| = (0.91 \pm 0.07) \times 10^{-28} \text{ m}^3 \text{ V}^{-2}$ and $|\chi^{(3)}_b| = (1.16 \pm 0.09) \times 10^{-19} \text{ m}^2 \text{ V}^{-2}$, which are comparable to the third-harmonic susceptibility of related semiconducting TMD and provide one step forward towards the complete characterization of the nonlinear optical properties of this family (MX₂; M = W, Mo; X = S, Se). The reliability of these values is supported by the good agreement of our values for $|\chi^{(2)}|$, extracted from the simultaneously recorded second-harmonic signal, with previous reports for the same material. The strong nonlinear response of WSe₂ in the infrared makes it a material suitable for applications in silicon photonics, all-optical switching and optical frequency conversion.

Materials and Methods

Sample fabrication and characterization. Flakes of WSe₂ were obtained via micromechanical exfoliation from a single bulk crystal and transferred onto a fused silica substrate. To prevent degradation, the sample was partially covered with multi-layer hBN. The sample's properties were characterized by photoluminescence, Raman spectroscopy and atomic force microscopy (for more details sample fabrication and characterization, see supporting information).

Experimental setup. Nonlinear optical properties of WSe₂ were investigated in a home-built multiphoton microscope setup. We used a half-waveplate to control the input linear polarization and a polarizer to analyze the harmonic signals. The pump laser was a 1545 nm, 200 fs, 80 MHz mode-locked fiber. A 100x objective lens focused the pump beam down to a spot size of $2 \mu\text{m}^2$. The step used in the sample displacement during spatial mapping was $0.5 \mu\text{m}$ (for more details on the experimental setup, see supporting information).

Data availability. The datasets generated during and/or analyzed during the current study are available from the corresponding author on reasonable request.

References

- Podzorov, V., Gershenson, M. E., Kloc, C., Zeis, R. & Bucher, E. High-mobility field-effect transistors based on transition metal dichalcogenides. *Appl. Phys. Lett.* **84**, 3301–3303 (2004).
- Yu, Z. *et al.* Analyzing the Carrier Mobility in Transition-Metal Dichalcogenide MoS₂ Field-Effect Transistors. *Adv. Funct. Mater.* **27**, 1604093 (2017).
- Mak, K. F., Lee, C., Hone, J., Shan, J. & Heinz, T. F. Atomically Thin MoS₂: A New Direct-Gap Semiconductor. *Phys. Rev. Lett.* **105**, 136805 (2010).
- Gutiérrez, H. R. *et al.* Extraordinary Room-Temperature Photoluminescence in Triangular WS₂ Monolayers. *Nano Lett.* **13**, 3447–3454 (2013).
- Tonndorf, P. *et al.* Photoluminescence emission and Raman response of monolayer MoS₂, MoSe₂, and WSe₂. *Opt. Express* **21**, 4908–4916 (2013).
- Splendiani, A. *et al.* Emerging Photoluminescence in Monolayer MoS₂. *Nano Lett.* **10**, 1271–1275 (2010).
- Ribeiro-Soares, J. *et al.* Second Harmonic Generation in WSe₂. *2D Mater.* **2**, 45015 (2015).

8. Malard, L. M. *et al.* Observation of intense second harmonic generation from MoS₂ atomic crystals. *Phys. Rev. B* **87**, 201401(R) (2013).
9. Reyes-Retana, J. A. & Cervantes-Sodi, F. Spin-orbital effects in metal-dichalcogenide semiconducting monolayers. *Sci. Rep.* **6**, 24093 (2016).
10. Zeng, H. *et al.* Optical signature of symmetry variations and spin-valley coupling in atomically thin tungsten dichalcogenides. *Sci. Rep.* **3**, 1608 (2013).
11. Xu, X., Yao, W., Xiao, D. & Heinz, T. F. Spin and pseudospins in layered transition metal dichalcogenides. *Nat. Phys.* **10**, 343–350 (2014).
12. Mak, K. F. & Shan, J. Photonics and optoelectronics of 2D semiconductor transition metal dichalcogenides. *Nat. Photonics* **10**, 216–226 (2016).
13. Wang, G. *et al.* Colloquium: Excitons in atomically thin transition metal dichalcogenides. *Rev. Mod. Phys.* **90**, 21001 (2018).
14. Janisch, C. *et al.* Extraordinary second harmonic generation in Tungsten Disulfide monolayers. *Sci. Rep.* **4**, 5530 (2014).
15. Le, C. T. *et al.* Nonlinear optical characteristics of monolayer MoSe₂. *Ann. Phys.* **528**, 551–559 (2016).
16. Kumar, N. *et al.* Second harmonic microscopy of monolayer MoS₂. *Phys. Rev. B* **87**, 161403 (2013).
17. Torres-Torres, C. *et al.* Third order nonlinear optical response exhibited by mono- and few-layers of WS₂. *2D Mater.* **3**, 21005 (2016).
18. Woodward, R. I. *et al.* Characterization of the second- and third-order nonlinear optical susceptibilities of monolayer MoS₂ using multiphoton microscopy. *2D Mater.* **4**, 11006 (2016).
19. Autere, A. *et al.* Nonlinear Optics with 2D Layered Materials. *Adv. Mater.* 1705963 (2018).
20. In the review paper published by Autere and collaborators (*Adv. Mater.* 1705963 (2018)), authors show values for third-harmonic susceptibilities of WSe₂ and MoSe₂, however such values are based on internal/unpublished data.
21. Karvonen, L. *et al.* Investigation of second- and third-harmonic generation in few-layer gallium selenide by multiphoton microscopy. *Sci. Rep.* **5**, 10334 (2015).
22. Boyd, R. W. *The Nonlinear Optical Susceptibility. Nonlinear Optics - Chapter 1* (Academic Press, 2008).
23. Kim, D. H. & Lim, D. Optical second-harmonic generation in few-layer MoSe₂. *J. Korean Phys. Soc.* **66**, 816–820 (2015).
24. Hsu, W.-T. *et al.* Second Harmonic Generation from Artificially Stacked Transition Metal Dichalcogenide Twisted Bilayers. **8**, 2951–2958 (2014).
25. Li, Y. *et al.* Probing symmetry properties of few-layer MoS₂ and h-BN by optical second-harmonic generation. *Nano Lett.* **13**, 3329–3333 (2013).
26. Li, D. *et al.* Multimodal Nonlinear Optical Imaging of MoS₂ and MoS₂-Based van der Waals Heterostructures. *ACS Nano* **10**, 3766–3775 (2016).
27. Rosa, H. G. *et al.* Second-Harmonic Spectroscopy for Defects Engineering Monitoring in Transition Metal Dichalcogenides. *Adv. Opt. Mater.* <https://doi.org/10.1002/adom.201701327> (2018).
28. Liu, H. *et al.* Fluorescence Concentric Triangles: A Case of Chemical Heterogeneity in WS₂ Atomic Monolayer. *Nano Lett.* **16**, 5559–5567 (2016).
29. Yu, H., Talukdar, D., Xu, W., Khurgin, J. B. & Xiong, Q. Charge-Induced Second-Harmonic Generation in Bilayer WSe₂. *Nano Lett.* **15**, 5653–5657 (2015).
30. Wang, R. *et al.* Third-harmonic generation in ultrathin films of MoS₂. *ACS Appl. Mater. Interfaces* **6**, 314–318 (2014).
31. Rodrigues, M. J. L. F. *et al.* Resonantly Increased Optical Frequency Conversion in Atomically Thin Black Phosphorus. *Adv. Mater.* **28**, 10693–10700 (2016).
32. Seyler, K. L. *et al.* Electrical control of second-harmonic generation in a WSe₂ monolayer transistor. *Nat. Nanotechnol.* **10**, 407–411 (2015).
33. Wang, G. *et al.* Giant Enhancement of the Optical Second-Harmonic Emission of WSe₂ Monolayers by Laser Excitation at Exciton Resonances. *Phys. Rev. Lett.* **114**, 97403 (2015).
34. Li, Y. *et al.* Measurement of the optical dielectric function of monolayer transition-metal dichalcogenides: MoS₂, MoSe₂, WS₂, and WSe₂. *Phys. Rev. B* **90**, 205422 (2014).
35. Fryett, T. K. *et al.* Silicon photonic crystal cavity enhanced second-harmonic generation from monolayer WSe₂. *2D Mater.* **4**, 15031 (2016).
36. Liu, L. *et al.* Enhanced optical Kerr nonlinearity of MoS₂ on silicon waveguides. *Photonics Res.* **3**, 206 (2015).
37. Youngblood, N. & Li, M. Integration of 2D materials on a silicon photonics platform for optoelectronics applications. *Nanophotonics* **6**, 1205–1218 (2017).
38. Wu, K. *et al.* All-optical phase shifter and switch near 1550 nm using tungsten disulfide (WS₂) deposited tapered fiber. *Opt. Express* **25**, 17639–17649 (2017).
39. Srivastava, Y. K. *et al.* MoS₂ for Ultrafast All-Optical Switching and Modulation of THz Fano Metaphotonic Devices. *Adv. Opt. Mater.* **5**, 1700762 (2017).

Acknowledgements

Y.W.H. acknowledges scholarship support from NGS. G.E. acknowledges financial support from National Research Foundation of Singapore (NRF Research Fellowship NRF-NRFF2011-02 and medium-sized centre programme) and Ministry of Education of Singapore (AcRF Tier 2 MOE2015-T2-2-123). V. M. P. acknowledges financial support from Ministry of Education of Singapore (FRC AcRF Tier 1 R-144-000-386-114). J.C.V.G. acknowledges financial support from CA2DM through National Research Foundation of Singapore (NRF-CRP Grant No. R-144-000-295-281).

Author Contributions

H.G.R. and Y. W. H. performed sample characterization, nonlinear optical experiments and analyzed the data. I.V. fabricated the hBN/WSe₂ sample. M.J.F.L.R. set up the multiphoton microscope system. T.T. and K.W. provided the hexagonal boron nitride flake. G.E., V.M.P. and J.C.V.G. supervised the work and revised the manuscript. All authors discussed and interpreted the results and contributed to the writing of the manuscript.

Additional Information

Supplementary information accompanies this paper at <https://doi.org/10.1038/s41598-018-28374-1>.

Competing Interests: The authors declare no competing interests.

Publisher's note: Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons license and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2018