

New Class of Betulinic Acid-Based Nanoassemblies of Cabazitaxel, Podophyllotoxin, and Thiolcolchicine

Eleonora Colombo, Laura Polito, Michele Biocotino, Paola Marzullo, Mariafrancesca Hyeraci, Lisa Dalla Via, and Daniele Passarella*

Cite This: *ACS Med. Chem. Lett.* 2020, 11, 895–898

Read Online


ACCESS |

Metrics & More

Article Recommendations

Supporting Information

ABSTRACT: Betulinic acid is validated as a new self-assembly inducer for the formation of nanoparticles (NPs) in combination with different drugs. The target compounds are characterized by the presence of anticancer drugs acting on tubulin dynamics and of a linker that could be a carbon chain or a triazole-based one. Nanoparticles formed are characterized and their biological activity is evaluated.



KEYWORDS: Self-assembled nanoparticles, cancer, betulinic acid, cabazitaxel, podophyllotoxin, thiolcolchicine

For several years we have been interested in the use of nanotechnology to improve the properties of both anticancer and neuroprotective drugs.^{1–8} We designed conjugates able to spontaneously assemble in water forming nanoparticles that can release the drug in cellular media,² fluorescent hetero-NPs,^{3,4} and hetero-NPs bearing two different drugs.^{4–6} These compounds present the general structure of a drug conjugated through a linker to a self-assembly inducer, that was either squalene,^{2–5} 4-(1,2-diphenylbut-1-en-1-yl)aniline,⁷ or 20-hydroxyecdysone.⁶ The choice of the self-assembly inducer is important for the formation of nanoparticles, and here is where we set our interest. In fact, the possibility to have a moiety that not only is able to induce the aggregation but also possesses some biological activity toward the same target could be useful to further improve the pharmacological properties of the drug.

Our goal was to identify a pharmacologically active compound that will be able to act as a self-assembly inducer in the formation of nanoparticles. Our previous results regarding the use of 20-hydroxyecdysone as a self-assembly inducer moved us to consider betulinic acid, a natural product derived from plane tree bark, that has shown beneficial properties for tumor therapy. In fact, the pentacyclic triterpenoid betulinic acid exhibits a wide range of biological and medicinal properties such as antivenom, anti-HIV, antibacterial, antimalarial, anti-inflammatory, anthelmintic, antinociceptive, anti-HSV-1, and anticancer activities.⁹ It has been reported to induce different forms of cell death, such as apoptosis, necrosis, and autophagy, in different types of cancers. In addition, nontumor cells, such as fibroblasts and lymphocytes, resulted less affected by betulinic acid than tumor

cells.¹⁰ The use of betulinic acid in nanoformulations is really interesting,¹¹ also because other pentacyclic triterpenoids were previously used as self-assembly inducers, like oleanolic acid and ursolic acid. We decided to consider betulinic acid for its possible dual activity (selective cytotoxic compound and self-assembly inducer) and to incorporate it in conjugated compounds using as second building block well-known tubulin binders (Figure 1). Synthesis of the planned compounds, their ability to form self-assembled nanoparticles and their ability to affect ovarian carcinoma cell viability are here reported.

To assess the capability of betulinic acid to act as a self-assembly inducer, we conjugated it to three different drugs, all interacting with microtubules as either stabilizers or destabilizers: *N*-desacetyl thiolcolchicine (2), cabazitaxel (3), and podophyllotoxin (4).

All these moieties were attached to betulinic acid through sebacic acid as a linker. Moreover, an additional triazole-based linker was used with *N*-desacetyl thiolcolchicine to verify its influence in the formation and in the biological properties of nanoparticles.¹² (Figure 2)

For this synthesis, betulinic acid needed to be modified, as its acidic moiety could give side reaction in the conjugation steps. It was reacted with trimethylsilyl diazomethane to form

Special Issue: In Memory of Maurizio Botta: His Vision of Medicinal Chemistry

Received: December 30, 2019

Accepted: February 28, 2020

Published: February 28, 2020






Figure 1. Structure of the designed conjugate compounds.





Figure 2. Structure of the conjugates.

its methyl ester **11**, that was subsequently used for the synthesis of the two series of conjugates. When sebacic acid was used as a linker, compound **11** was conjugated to a monoprotected sebacic acid to give product **13** that, upon deprotection by TBAF, gave us the desired betulinic acid-linker **14**. This moiety was then conjugated, under the same conditions, to the three above-mentioned drugs, leading to final compounds **7**, **8**, and **9** (Scheme 1).

For what regards the conjugate bearing the triazole moiety, instead, compound **11** was reacted with acyl chloride **15** (prepared following a procedure already reported in the literature¹³) to give the corresponding ester. Meanwhile, the chosen drug, i.e. *N*-desacetyl thiocolchicine, was conjugated to **17**, thus obtaining azide **18**. Having in our hands the azide and the alkyne moieties, we performed a 1,3-dipolar cycloaddition to obtain triazole **10** as the final compound (Scheme 2).


Synthesized all the desired conjugates, we evaluated the successful formation of nanoparticles by dynamic light scattering (DLS) measurements (Table 1). All the compounds gave a stable and monodisperse suspension of NPs, characterized by hydrodynamic diameters (HD) in the range of 320–560 nm and a negative Z-potential (<−25.0 mV).

Scheme 1. Synthesis of Conjugates with Sebacic Linker^a



^aReaction conditions: (a) $(\text{CH}_3)_3\text{SiCHN}_2$, MeOH/PhCH₃, rt, 30 h, 95%; (b) DCC, DMAP, CH₂Cl₂, rt, overnight, 92%; (c) TBAF, THF, rt, 20 h, 93%; (d) drug, DCC, DMAP, CH₂Cl₂, rt, 26 h, 66–95%.

Scheme 2. Synthesis of Thiocolchicine–Triazole Conjugate



a) DIPEA, PPy, 0°C to rt, 80%; b) DCC, DMAP, CH₂Cl₂, 20h, quant; c) CuSO₄·5H₂O, sodium ascorbate, DABCO, AcOH, H₂O/t-BuOH 1.2:1, 3h, 51%.

Table 1. Hydrodynamic Diameter and Z-Potential of Nanoformulated Compounds **7**, **8**, **9**, and **10**

Compound	Polidispersity index (PI)	Hydrodynamic Diameters (nm)	Z-Potential (mV)
7	0.088 ± 0.022	322 ± 11	−34.02 ± 0.48
8	0.126 ± 0.010	503 ± 104	−35.53 ± 0.51
9	0.074 ± 0.012	558 ± 49	−41.03 ± 0.65
10	0.173 ± 0.015	329 ± 59	−25.66 ± 3.84

The ability of the building blocks (desacetylthiocolchicine, podophyllotoxin, and cabazitaxel) of conjugates and of the NPs to affect cell viability was assayed by trypan blue exclusion test

on ovarian carcinoma cell line, A2780. The obtained results, expressed as GI_{50} values (μM), are shown in Table 2.

Table 2. Cell Growth Inhibition of A2780 Cells in the Presence of Tested Compounds and NPs

Compound	A2780 cells (GI_{50} μM) ^a
<i>N</i> -Desacetylthiocolchicine (2)	0.0121 ± 0.0003
10	2.6 ± 0.1
NP-10	3.0 ± 0.1
9	14.5 ± 0.6
NP-9	9.5 ± 1.2
Podophyllotoxin (4)	0.0085 ± 0.0005
7	16.9 ± 0.3
NP-7	17.0 ± 3.2
Cabazitaxel (3)	0.000327 ± 0.000023
8	0.35 ± 0.01
NP-8	12.0 ± 2.3
Betulinic methyl ester (11)	17.6 ± 1.7

^aValues are the mean ± SD of at least three independent experiments.

All starting drugs are very effective in inducing cytotoxicity, as expected, with GI_{50} values in the nanomolar range. Otherwise, 11, the methyl ester of betulinic acid, appears significantly less active. Interestingly, the antiproliferative capacity is similarly maintained both by the conjugates as monomers and by the corresponding NPs, even though to a lesser extent than native drugs. Indeed, for all NPs GI_{50} values in the micromolar range were obtained. In particular, 10 and 9 exert the highest cytotoxicity, while 8 formulated as a nanoparticle demonstrates the most pronounced decrease in biological effect with respect to the starting cabazitaxel, by about 5 orders of magnitude. This result may be attributed to a slower disaggregation of the nanoparticles or cleavage of the ester moiety. Moreover, the difference in antiproliferative effect between 10 and 9 is noteworthy. In detail, 10 shows a GI_{50} value about three times lower than that of 9, which highlights the crucial role played by the linker and, in particular, by the insertion of the triazole moiety.

The maintenance of the cytotoxic effect by the NPs prompts us to investigate if the mechanism of action is also retained. For this purpose, cytofluorimetric analyses were performed on A2780 stained with propidium iodide and incubated with test agents, and the effect on cell cycle was examined. The cytograms of DNA content and the percentages of cells in the different phases of cell cycle are reported in Figure 3a–b and in Table 3 and Table 4. The obtained results indicate that the NPs are able to induce an increase in G₂/M, thus acting, in accordance with the starting drugs, as microtubule-targeting agents.

CONCLUSIONS

A class of betulinic acid-based conjugate compounds of cabazitaxel, podophyllotoxin, and thiocolchicine were prepared. The obtained compounds self-assemble and form nanoassemblies that we characterized in this study. Both the conjugates as monomers and the relative nanoparticles were tested for their antiproliferative activity, obtaining good results even though all the products result less active than the native drugs. In particular, while the thiocolchicine-based conjugates maintain an interesting activity, especially the compound that presents the triazole ring-based linker, the one bearing cabazitaxel was the most affected by the conjugation. A




Figure 3. (a–b) Cell cycle distribution of A2780 cells incubated in the presence of the test agents for 24 h at the indicated concentrations.

Table 3. Data Relative to Figure 3a

	Control	<i>N</i> -Desac. (2) [40 nM]	10 [5 μM]	9 [30 μM]
PreG ₀	0.6%	15.5%	6.5%	6.2%
G ₀ /G ₁	69.1%	11.4%	15.8%	17.2%
S	12.8%	16.7%	10%	8.7%
G ₂ /M	17.2%	55.8%	67.1%	67.4%

Table 4. Data Relative to Figure 3b

	Podop. (4) [15 nM]	7 [40 μM]	Cabaz. (3) [7.5 nM]	8 [30 μM]
PreG ₀	9.8%	4.2%	17.4%	12.4%
G ₀ /G ₁	39.4%	56.9%	30.8%	30.5%
S	16.7%	11.5%	15.8%	26.4%
G ₂ /M	33.2%	27.3%	35.5%	30.5%

reasonable explanation of that can be attributed to a sluggish disaggregation of said nanoparticles, to a limited interaction of

the drug conjugate or to a partial hydrolysis of the ester bond that connects the native drug to the linker. We consider relevant that the studies regarding the biological mechanism inducing the detected cytotoxicity show an increase in G2/M, that confirms the maintenance of the activity of the native microtubules-tubulin binders cabazitaxel, podophyllotoxin, and thiocolchicine. The introduction of a proper self-immolative linker could secure the release of the native drugs and the improvement of the biological activity. The described results are a further demonstration of the easy obtainment of self-assembled nanoparticles by simple chemical functionalization of known anticancer drugs and of the possible modulation of their activity by varying the nature of the self-assembly inducer and linker.

■ ASSOCIATED CONTENT

SI Supporting Information

The Supporting Information is available free of charge at <https://pubs.acs.org/doi/10.1021/acsmchemlett.9b00668>.

Experimental details regarding synthesis of conjugates, nanoparticles preparation and characterization, and biological evaluation (PDF)

■ AUTHOR INFORMATION

Corresponding Author

Daniele Passarella – Dipartimento di Chimica, Università degli Studi di Milano, 20133 Milano, Italy; orcid.org/0000-0001-6180-9581; Email: daniele.passarella@unimi.it

Authors

Eleonora Colombo – Dipartimento di Chimica, Università degli Studi di Milano, 20133 Milano, Italy

Laura Polito – CNR-ISTM, 20138 Milano, Italy; orcid.org/0000-0002-7756-2365

Michele Biocotino – Dipartimento di Chimica, Università degli Studi di Milano, 20133 Milano, Italy

Paola Marzullo – Dipartimento di Chimica, Università degli Studi di Milano, 20133 Milano, Italy

Mariafrancesca Hyeraci – Dipartimento di Scienze del Farmaco, Università degli Studi di Padova, 35131 Padova, Italy

Lisa Dalla Via – Dipartimento di Scienze del Farmaco, Università degli Studi di Padova, 35131 Padova, Italy; orcid.org/0000-0002-9828-9388

Complete contact information is available at:

<https://pubs.acs.org/doi/10.1021/acsmchemlett.9b00668>

Notes

The authors declare no competing financial interest.

■ REFERENCES

- (1) Fumagalli, G.; Marucci, C.; Christodoulou, M. S.; Stella, B.; Dosio, F.; Passarella, D. Self Assembly Drug Conjugates for Anticancer Treatment. *Drug Discovery Today* **2016**, *21*, 1321–1329.
- (2) Borrelli, S.; Christodoulou, M. S.; Ficarra, I.; Silvani, A.; Cappelletti, G.; Cartelli, D.; Damia, G.; Ricci, F.; Zucchetti, M.; Dosio, F.; Passarella, D. New Class of Squalene-Based Releasable Nanoassemblies of Paclitaxel, Podophyllotoxin, Camptothecin and Epothilone A. *Eur. J. Med. Chem.* **2014**, *85*, 179–190.
- (3) Borrelli, S.; Cartelli, D.; Secundo, F.; Fumagalli, G.; Christodoulou, M. S.; Borroni, A.; Perdicchia, D.; Dosio, F.; Milla, P.; Cappelletti, G.; Passarella, D. Self-Assembled Squalene-based Fluorescent Hetero-nanoparticles. *ChemPlusChem* **2015**, *80*, 47–49.

- (4) Fumagalli, G.; Mazza, D.; Christodoulou, M. S.; Damia, G.; Ricci, F.; Perdicchia, D.; Stella, B.; Dosio, F.; Sotiropoulou, P. A.; Passarella, D. Cyclopamine–Paclitaxel-Containing Nanoparticles: Internalization in Cells Detected by Confocal and Super Resolution Microscopy. *ChemPlusChem* **2015**, *80*, 1380–1383.

- (5) Fumagalli, G.; Stella, B.; Pastushenko, I.; Ricci, F.; Christodoulou, M. S.; Damia, G.; Mazza, D.; Arpicco, S.; Giannini, C.; Morosi, L.; Dosio, F.; Sotiropoulou, P. A.; Passarella, D. *ACS Med. Chem. Lett.* **2017**, *8*, 953–957.

- (6) Fumagalli, G.; Giorgi, G.; Vágvölgyi, M.; Colombo, E.; Christodoulou, M. S.; Collico, V.; Prosperi, D.; Dosio, F.; Hunyadi, A.; Montopoli, M.; Hyeraci, M.; Silvani, A.; Lesma, G.; Dalla Via, L.; Passarella, D. Heteronanoparticles by self-assembly of ecdysteroid and doxorubicin conjugates to overcome cancer resistance. *ACS Med. Chem. Lett.* **2018**, *9*, 468–471.

- (7) Fumagalli, G.; Christodoulou, M. S.; Riva, B.; Revuelta, I.; Marucci, C.; Collico, V.; Prosperi, D.; Riva, S.; Perdicchia, D.; Bassanini, I.; García-Argáez, A.; Dalla Via, L.; Passarella, D. Self-assembled 4-(1,2-diphenylbut-1-en-1-yl)aniline based Nanoparticles: Podophyllotoxin and Aloin as building blocks. *Org. Biomol. Chem.* **2017**, *15*, 1106–1109.

- (8) Colombo, E.; Biocotino, M.; Frapporti, G.; Piccoli, G.; Randazzo, P.; Christodoulou, M. S.; Polito, L.; Seneci, P.; Passarella, D. Nanolipid-Trehalose Conjugates and Nano-Assemblies as Putative Autophagy Inducers. *Pharmaceutics* **2019**, *11*, 422–438.

- (9) Hordyjewska, A.; Ostapiuk, A.; Horecka, A.; Kurzepa, J. Betulin and betulinic acid: triterpenoids derivatives with a powerful biological potential. *Phytochem. Rev.* **2019**, *18*, 929–951.

- (10) Zuco, V.; Supino, R.; Righetti, S. C.; Cleris, L.; Marchesi, E.; Gambacorti-Passerini, C.; Formelli, F. Selective cytotoxicity of betulinic acid on tumor cell lines, but not on normal cells. *Cancer Lett.* **2002**, *175*, 17–25.

- (11) Saneja, A.; Arora, D.; Kumar, R.; Dubey, R. D.; Panda, A. K.; Gupta, P. N. Therapeutic applications of betulinic acid nano-formulations. *Ann. N. Y. Acad. Sci.* **2018**, *1421*, 5–18.

- (12) Bonandi, E.; Christodoulou, M. S.; Fumagalli, G.; Perdicchia, D.; Rastelli, G.; Passarella, D. 1,2,3-Triazole ring as bioisostere in medicinal chemistry. *Drug Discovery Today* **2017**, *22*, 1572–1581.

- (13) Menchon, G.; Prota, A. E.; Lucena-Agell, D.; Bucher, P.; Jansen, R.; Irschik, H.; Muller, R.; Paterson, I.; Diaz, J. F.; Altmann, K.-H.; Steinmetz, M. O. A fluorescence anisotropy assay to discover and characterize ligands targeting the maytansine site of tubulin. *Nat. Commun.* **2018**, *9*, 1–9.