alignment, CG content and conservation of a random 60 AluYg(s)