

Supplementary Table 2. Effective diameters of NPs formulated with different supercoiled content of pDNA.

Supercoiled content of pDNA (%)	Average D_{Eff} by DLS \pm SD (nm)
8	145 \pm 8
12	164 \pm 3
17	143 \pm 2
31	136 \pm 4
55	148 \pm 4
75	190 \pm 1
81	130 \pm 7
95	130 \pm 5