

Supplementary Table 3. Effective diameters of NPs formulated with different molar ratio of the pDNA and PEIm components.

N/P ratio	Average D_{Eff} by DLS \pm SD (nm)
1	188 \pm 58
2	117 \pm 4
3	128 \pm 5
4	104 \pm 2
5	101 \pm 2
6	110 \pm 7