

Copyright WILEY-VCH Verlag GmbH & Co. KGaA, 69469 Weinheim, Germany,
2014.

Supporting Information

for *Adv. Funct. Mater.*, DOI: 10.1002/adfm.((please add manuscript number))

Title: Injectable Peptide Decorated Functional Nanofibrous Hollow Microspheres to Direct Stem Cell Differentiation for Tissue Regeneration

Zhanpeng Zhang, Melanie J. Gupte, Xiaobing Jin and Peter X. Ma*




Figure S1. NMR spectrum of macromonomer HEMA-PLLA5. ¹H NMR (400 MHz, CDCl₃, δ): 6.10 (s, 2H, a), 5.17 (q, J = 8 Hz, 1H; e), 4.25 (m, 5H; c+d+h), 2.01 (s, 3H, b), 1.38 (d, J = 8Hz, 3H; f), 1.35 (d, J = 8Hz, 3H; g).




Figure S2. NMR spectrum of graft copolymer PHEMA10-g-PLLA5. ^1H NMR (400 MHz, CDCl_3 , δ): 5.17 (q, $J = 8$ Hz, 1H; e), 4.30 (m, 10H; c+d+h+j+k+l), 2.41 (s, 2H, i), 1.58 (d, $J = 8$ Hz, 3H; f), 1.35 (d, $J = 8$ Hz, 3H; g), 1.01 (s, 3H, b).




Figure S3. NMR spectrum of functionalized graft copolymer PHEMA-g-PLLA-alkene. ^1H NMR (400 MHz, CDCl_3 , δ): 6.11 (m, 3H, m+n), 5.17 (q, $J = 8$ Hz, 1H; e), 4.10 (m, 9H; c+d+h+j+k), 2.62 (s, 2H, i), 1.65 (d, $J = 8$ Hz, 3H; f), 1.30 (d, $J = 8$ Hz, 3H; g), 0.98 (s, 3H, b).




Figure S4. SEM of FNF-HMS after click reaction with GF-mimicking peptide CM10.




Figure S5. a, b) SEM graphs of BMSCs seeded on FNF-HMS for 1 day. BMSCs attached to both the outside (a) and inside (b) of the microspheres. Scale bar: 20 μm. c) Confocal images of BMSCs seeded on FNF-HMS for 1 week, showing that many cells were able to adhere to the inside of the microspheres. Blue: nuclei; red: F-actin.