

Supplementary Materials: Intrinsic Flame-Retardant and Thermally Stable Epoxy Endowed by a Highly Efficient, Multifunctional Curing Agent

Chunlei Dong, Alvianto Wirasaputra, Qinqin Luo, Shumei Liu, Yanchao Yuan, Jianqing Zhao and Yi Fu




Figure S1. FTIR spectra of DPPA, HB, and HB-DPPA.




Figure S2. DSC thermograms of EP-0 and EP-2 at a heating rate of 5 °C/min.

Table S1. Curing parameters of EP-0 and EP-2.

Sample ID	T ₀ (°C)	T _p (°C)	T _e (°C)
EP-0	69.1	145.4	238.4
EP-2	54.5	132.1	215.7




Figure S3. DSC thermogram of DGEBA/HB-DPPA at a heating rate of 5 °C/min.