

Attachment B – Assessment criteria by Frencken and Holmgren (2001)

Score	Criteria
0	Present, good
1	Present, slight marginal defect for whatever reason, at any one place, which is less than 0.5 mm in depth. No repair is needed
2	Present, marginal defect for whatever reason, at any one place which is deeper than 0.5 mm but less than 1.0 mm. Repair is needed
3	Present, gross defect of more than 1.0 mm in depth. Repair is needed
4	Not present, restoration has (almost) completely disappeared. Treatment is needed
5	Not present, other restorative treatment has been performed
6	Not present, tooth has been extracted
7	Present, wear and tear gradually over larger parts of the restoration but are less than 0.5 mm at the deepest point. No repair is needed
8	Present, wear and tear gradually over larger parts of the restoration which are deeper than 0.5 mm. Repair is needed
9	Unable to diagnose

Note: Restorations considered to have survived are scored by codes: 0, 1 and 7; those considered to have failed by codes: 2, 3, 4 and 8; while those that are considered to be unrelated to success and failure are coded: 5 and 6.