

Attachment C – Assessment criteria by Roeleveld et al. (2006)

Score	Criteria
00	Restoration still present, correct
10	Restoration present, slight defect at the margin and/or wear of the surface; < 0.5 mm in depth, repair needed
11	Restoration present, defect at the margin and/or wear of the surface; > 0.5 mm in depth, repair needed
12	Restoration present; underfilled > 0.5 mm, no gap, repair needed
13	Restoration overfilled > 0.5 mm, repair needed
20	Secondary caries, discoloration in depth, surface hard and intact, caries within dentin; repair needed
21	Secondary caries. Surface defect, caries within dentin; repair needed
30	Restoration not present, bulk fracture, loose, (partly) lost; repair needed (if still possible without exposing the pulp)
40	Inflammation of the pulp (restoration still in situ, not categorized in the former categories); fistula or severe pain complaints; extraction needed
50	Tooth not present because of extraction
60	Tooth not present because of shedding
70	Tooth not present because of extraction
90	Patient not present

Note: Restorations considered to have survived are scored by codes: 00 and 10; those considered to have by code: 11, 12, 13, 20, 21, 30 or 40; while those considered to be unrelated to success and failure are coded: 50, 60, 70 or 90