

Supplementary Table 2. Effect of 24 hours of incubation of alveolar basal epithelial A549 and microglial BV-2 cells with 2 $\mu\text{g/ml}$ of engineered carbon nanodiamonds (ECNs) on cell death.

% of cell death			
A549		BV-2	
Resting	ECNs	Resting	ECNs
1.52 (0.39)	2.70 (0.45)	2.21 (1.82)	2.76 (1.20)

Values are the mean of four different experiments. Standard deviations are in parenthesis.