

checkCIF/PLATON report

Structure factors have been supplied for datablock(s) Coesite-IV_40.2GPa

THIS REPORT IS FOR GUIDANCE ONLY. IF USED AS PART OF A REVIEW PROCEDURE FOR PUBLICATION, IT SHOULD NOT REPLACE THE EXPERTISE OF AN EXPERIENCED CRYSTALLOGRAPHIC REFEREE.

No syntax errors found. CIF dictionary Interpreting this report

Datablock: Coesite-IV_40.2GPa

Bond precision: Si- O = 0.0095 A Wavelength=0.41273

Cell: a=6.5989(8) b=7.000(2) c=8.649(3)
 alpha=69.14(3) beta=83.153(16) gamma=81.801(16)
Temperature: 296 K

	Calculated	Reported
Volume	368.50(19)	368.46(17)
Space group	P -1	P -1
Hall group	-P 1	-P 1
Moiety formula	O16 Si8	O2 Si
Sum formula	O16 Si8	O2 Si
Mr	480.72	60.09
Dx,g cm-3	4.333	4.333
Z	2	16
Mu (mm-1)	0.376	0.376
F000	480.0	480.0
F000'	480.43	
h,k,lmax	10,11,14	10,8,11
Nref	3314	900
Tmin,Tmax		0.006,1.000
Tmin'		

Correction method= # Reported T Limits: Tmin=0.006 Tmax=1.000
AbsCorr = MULTI-SCAN

Data completeness= 0.272 Theta(max)= 19.601

R(reflections)= 0.0884(789) wR2(reflections)= 0.2599(900)

S = 1.109 Npar= 97

The following ALERTS were generated. Each ALERT has the format
test-name_ALERT_alert-type_alert-level.
Click on the hyperlinks for more details of the test.


 **Alert level A**

ATOM007_ALERT_1_A _atom_site_aniso_label is missing
Unique label identifying the atom site.

Author Response: Due to incompleteness of the dataset thermal parameters were refined in isotropic approximation.

PLAT029_ALERT_3_A _diffrn_measured_fraction_theta_full value Low . 0.421 Why?

Author Response: The dataset was incomplete since the data were collected in a diamond anvil cell metallic body of which shadows more than 60% of the reflections.

 **Alert level B**

PLAT911_ALERT_3_B Missing FCF Refl Between Thmin & STh/L= 0.600 754 Report

Author Response: Certain part of the reflections is missing due to geometry of the experiment. The metallic body of the diamond anvil cell absorbs more than 60% of the reflections.

 **Alert level C**

DIFMX02_ALERT_1_C The maximum difference density is > 0.1*ZMAX*0.75
The relevant atom site should be identified.

PLAT084_ALERT_3_C High wR2 Value (i.e. > 0.25)	0.26	Report
PLAT088_ALERT_3_C Poor Data / Parameter Ratio	9.28	Note
PLAT097_ALERT_2_C Large Reported Max. (Positive) Residual Density	1.40	eA-3
PLAT906_ALERT_3_C Large K Value in the Analysis of Variance	3.148	Check
PLAT939_ALERT_3_C Large Value of Not (SHELXL) Weight Optimized S .	10.10	Check

 **Alert level G**

ABSMU01_ALERT_1_G Calculation of _exptl_absorpt_correction_mu
not performed for this radiation type.

PLAT004_ALERT_5_G Polymeric Structure Found with Maximum Dimension	3	Info
PLAT042_ALERT_1_G Calc. and Reported MoietyFormula Strings Differ	Please	Check
PLAT045_ALERT_1_G Calculated and Reported Z Differ by a Factor ...	0.13	Check
PLAT072_ALERT_2_G SHELXL First Parameter in WGHT Unusually Large	0.19	Report
PLAT152_ALERT_1_G The Supplied and Calc. Volume s.u. Differ by ...	2	Units
PLAT396_ALERT_2_G Deviating Si-O-Si Angle From 150 for O4	128.1	Degree
PLAT396_ALERT_2_G Deviating Si-O-Si Angle From 150 for O10	121.9	Degree
PLAT396_ALERT_2_G Deviating Si-O-Si Angle From 150 for O11	132.1	Degree
PLAT432_ALERT_2_G Short Inter X...Y Contact Si1 ..015	3.22	Ang.
PLAT432_ALERT_2_G Short Inter X...Y Contact Si3 ..09	3.22	Ang.
PLAT432_ALERT_2_G Short Inter X...Y Contact Si4 ..07	3.31	Ang.
PLAT432_ALERT_2_G Short Inter X...Y Contact Si4 ..Si6	3.50	Ang.
PLAT432_ALERT_2_G Short Inter X...Y Contact Si5 ..09	3.13	Ang.
PLAT432_ALERT_2_G Short Inter X...Y Contact Si5 ..010	3.30	Ang.

PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si6	..Si6	2.82	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si6	..O11	3.37	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si7	..O3	3.14	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si7	..O9	3.16	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si7	..Si8	3.16	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si7	..O6	3.27	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si8	..O16	3.10	Ang.
PLAT432_ALERT_2_G	Short Inter X...Y Contact	Si8	..O15	3.38	Ang.
PLAT910_ALERT_3_G	Missing # of FCF Reflection(s) Below Theta(Min).			1	Note
PLAT912_ALERT_4_G	Missing # of FCF Reflections Above STh/L= 0.600			1219	Note
PLAT933_ALERT_2_G	Number of OMIT Records in Embedded .res File ...			6	Note
PLAT951_ALERT_5_G	Calculated (ThMax) and CIF-Reported Kmax Differ			3	Units
PLAT952_ALERT_5_G	Calculated (ThMax) and CIF-Reported Lmax Differ			3	Units
PLAT957_ALERT_1_G	Calculated (ThMax) and Actual (FCF) Kmax Differ			3	Units
PLAT958_ALERT_1_G	Calculated (ThMax) and Actual (FCF) Lmax Differ			3	Units

2 **ALERT level A** = Most likely a serious problem - resolve or explain
1 **ALERT level B** = A potentially serious problem, consider carefully
6 **ALERT level C** = Check. Ensure it is not caused by an omission or oversight
30 **ALERT level G** = General information/check it is not something unexpected

8 ALERT type 1 CIF construction/syntax error, inconsistent or missing data
20 ALERT type 2 Indicator that the structure model may be wrong or deficient
7 ALERT type 3 Indicator that the structure quality may be low
1 ALERT type 4 Improvement, methodology, query or suggestion
3 ALERT type 5 Informative message, check

It is advisable to attempt to resolve as many as possible of the alerts in all categories. Often the minor alerts point to easily fixed oversights, errors and omissions in your CIF or refinement strategy, so attention to these fine details can be worthwhile. In order to resolve some of the more serious problems it may be necessary to carry out additional measurements or structure refinements. However, the purpose of your study may justify the reported deviations and the more serious of these should normally be commented upon in the discussion or experimental section of a paper or in the "special_details" fields of the CIF. checkCIF was carefully designed to identify outliers and unusual parameters, but every test has its limitations and alerts that are not important in a particular case may appear. Conversely, the absence of alerts does not guarantee there are no aspects of the results needing attention. It is up to the individual to critically assess their own results and, if necessary, seek expert advice.

Publication of your CIF in IUCr journals

A basic structural check has been run on your CIF. These basic checks will be run on all CIFs submitted for publication in IUCr journals (*Acta Crystallographica*, *Journal of Applied Crystallography*, *Journal of Synchrotron Radiation*); however, if you intend to submit to *Acta Crystallographica Section C* or *E* or *IUCrData*, you should make sure that full publication checks are run on the final version of your CIF prior to submission.

Publication of your CIF in other journals

Please refer to the *Notes for Authors* of the relevant journal for any special instructions relating to CIF submission.

PLATON version of 30/01/2018; check.def file version of 30/01/2018

Datablock Coesite-IV_40.2GPa - ellipsoid plot

