checkCIF/PLATON report

Structure factors have been supplied for datablock(s) Coesite-IV_49.31GPa

THIS REPORT IS FOR GUIDANCE ONLY. IF USED AS PART OF A REVIEW PROCEDURE FOR PUBLICATION, IT SHOULD NOT REPLACE THE EXPERTISE OF AN EXPERIENCED CRYSTALLOGRAPHIC REFEREE.

Datablock: Coesite-IV_49.31GPa

```
Bond precision: Si- O = 0.0071 A
                                       Wavelength=0.28965
Cell:
             a=6.5175(8) b=6.8754(12) c=8.4943(15)
             alpha=69.612(16) beta=83.289(12) gamma=81.990(12)
Temperature: 296 K
               Calculated
                                        Reported
Volume
              352.35(10)
                                        352.35(10)
Space group
                                        P -1
             P -1
Hall group
              -P 1
                                        -P 1
Moiety formula 016 Si8
                                        02 Si
Sum formula
             016 Si8
                                        02 Si
Mr
              480.72
                                        60.09
              4.531
                                        4.531
Dx,g cm-3
               2
Ζ
                                        16
Mu (mm-1)
              0.188
                                        0.188
F000
               480.0
                                        480.0
F000′
               480.04
h,k,lmax
               10,10,13
                                        10,9,11
Nref
               2690
                                        968
                                        0.190,1.000
Tmin,Tmax
Tmin'
Correction method= # Reported T Limits: Tmin=0.190 Tmax=1.000
AbsCorr = MULTI-SCAN
Data completeness= 0.360
                                Theta(max) = 12.872
R(reflections) = 0.0628(798) wR2(reflections) = 0.1740(968)
S = 1.124
                         Npar= 97
```

The following ALERTS were generated. Each ALERT has the format test-name_ALERT_alert-type_alert-level.

Click on the hyperlinks for more details of the test.

🗣 Alert level A

ATOM007_ALERT_1_A _atom_site_aniso_label is missing Unique label identifying the atom site.

Author Response: Due to incompleteness of the dataset thermal parameters were refined in isotropic approximation.

PLAT029_ALERT_3_A _diffrn_measured_fraction_theta_full value Low . 0.366 Why?

Author Response: The dataset was incomplete since the data were collected in a diamond anvil cell metallic body of which shadows more than 60% of the reflections.

Alert level B

PLAT911_ALERT_3_B Missing FCF Refl Between Thmin & STh/L= 0.600 795 Report

Author Response: Certain part of the reflections is missing due to geometry of the experiment. The metallic body of the diamond anvil cell absorbs more than 60% of the reflections.

→ Alert level C		
PLAT088_ALERT_3_C Poor Data / Parameter Ratio	9.98	Note
PLAT906_ALERT_3_C Large K Value in the Analysis of Variance 8	3.480	Check
PLAT910_ALERT_3_C Missing # of FCF Reflection(s) Below Theta(Min).	8	Note
PLAT975_ALERT_2_C Check Calcd Resid. Dens. 0.46A From 010	0.48	eA-3

Alert level G

 $\begin{tabular}{ll} ABSMU01_ALERT_1_G & Calculation of $\tt exptl_absorpt_correction_mu \\ & not performed for this radiation type. \end{tabular}$

PLAT004_ALERT_5_G Polymeric Structure Found with Maximum Dimension	3 Info	
PLAT012_ALERT_1_G N.O.Kshelx_res_checksum Found in CIF	Please Chec	k
PLAT042_ALERT_1_G Calc. and Reported MoietyFormula Strings Differ	Please Chec	k
PLAT045_ALERT_1_G Calculated and Reported Z Differ by a Factor	0.13 Chec	k
PLAT072_ALERT_2_G SHELXL First Parameter in WGHT Unusually Large	0.10 Repo	rt
PLAT396_ALERT_2_G Deviating Si-O-Si Angle From 150 for O4	126.5 Degr	ee
PLAT396_ALERT_2_G Deviating Si-O-Si Angle From 150 for 010	119.8 Degr	ee
PLAT396_ALERT_2_G Deviating Si-O-Si Angle From 150 for O11	129.9 Degr	ee
PLAT432_ALERT_2_G Short Inter XY Contact Sil015	3.18 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si407	3.27 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si4Si6	3.42 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si509	3.08 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si5010	3.24 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si703	3.10 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si7Si8	3.13 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si709	3.13 Ang.	
PLAT432_ALERT_2_G Short Inter XY Contact Si706	3.21 Ang.	

```
PLAT432_ALERT_2_G Short Inter X...Y Contact Si8
                                                   ..016
                                                                       3.03 Ang.
                                                    ..015
PLAT432_ALERT_2_G Short Inter X...Y Contact Si8
                                                                      3.34 Ang.
PLAT912_ALERT_4_G Missing # of FCF Reflections Above STh/L= 0.600
                                                                      830 Note
PLAT913_ALERT_3_G Missing # of Very Strong Reflections in FCF ....
                                                                         2 Note
PLAT933_ALERT_2_G Number of OMIT Records in Embedded .res File ...
                                                                         9 Note
PLAT952_ALERT_5_G Calculated (ThMax) and CIF-Reported Lmax Differ
                                                                         2 Units
PLAT958_ALERT_1_G Calculated (ThMax) and Actual (FCF) Lmax Differ
                                                                         2 Units
```

```
2 ALERT level A = Most likely a serious problem - resolve or explain
1 ALERT level B = A potentially serious problem, consider carefully
4 ALERT level C = Check. Ensure it is not caused by an omission or oversight
25 ALERT level G = General information/check it is not something unexpected

6 ALERT type 1 CIF construction/syntax error, inconsistent or missing data
17 ALERT type 2 Indicator that the structure model may be wrong or deficient
6 ALERT type 3 Indicator that the structure quality may be low
1 ALERT type 4 Improvement, methodology, query or suggestion
2 ALERT type 5 Informative message, check
```

It is advisable to attempt to resolve as many as possible of the alerts in all categories. Often the minor alerts point to easily fixed oversights, errors and omissions in your CIF or refinement strategy, so attention to these fine details can be worthwhile. In order to resolve some of the more serious problems it may be necessary to carry out additional measurements or structure refinements. However, the purpose of your study may justify the reported deviations and the more serious of these should normally be commented upon in the discussion or experimental section of a paper or in the "special_details" fields of the CIF. checkCIF was carefully designed to identify outliers and unusual parameters, but every test has its limitations and alerts that are not important in a particular case may appear. Conversely, the absence of alerts does not guarantee there are no aspects of the results needing attention. It is up to the individual to critically assess their own results and, if necessary, seek expert advice.

Publication of your CIF in IUCr journals

A basic structural check has been run on your CIF. These basic checks will be run on all CIFs submitted for publication in IUCr journals (*Acta Crystallographica*, *Journal of Applied Crystallography*, *Journal of Synchrotron Radiation*); however, if you intend to submit to *Acta Crystallographica Section C* or *E* or *IUCrData*, you should make sure that full publication checks are run on the final version of your CIF prior to submission.

Publication of your CIF in other journals

Please refer to the *Notes for Authors* of the relevant journal for any special instructions relating to CIF submission.

PLATON version of 30/01/2018; check.def file version of 30/01/2018

