

Application of Targeted Molecular and Material Property Optimization to Bacterial Attachment-Resistant (Meth)acrylate Polymers

Kevin Adlington,[†] Nam T. Nguyen,^{†,‡} Elizabeth Eaves,^{†,‡} Jing Yang,[§] Chien-Yi Chang,^{§,||} Jianing Li,^{†,‡} Alexandra L. Gower,[†] Amy Stimpson,[†] Daniel G. Anderson,[⊥] Robert Langer,[⊥] Martyn C. Davies,[#] Andrew L. Hook,[#] Paul Williams,[§] Morgan R. Alexander,[#] and Derek J. Irvine^{*,†}

[†]Department of Chemical and Environmental Engineering, Faculty of Engineering, [‡]School of Chemistry, [§]Centre for Biomolecular Sciences and School of Life Sciences, School of Chemistry, and [#]Laboratory of Biophysics and Surface Analysis, School of Pharmacy, University of Nottingham, Nottingham, NG7 2RD, United Kingdom

[⊥]Department of Chemical Engineering, Institute for Medical Engineering and Science, Harvard-MIT Division of Health Sciences and Technology, David H. Koch Institute for Integrative Cancer Research, Massachusetts Institute of Technology, 500 Main Street, Cambridge, Massachusetts 02139, United States




Figure S1 – ¹H NMR spectrum of precipitated IBMA:DEGMA 75/25 (300 MHz, CDCl₃). Integral Ha = 0.577; integral 2Hb = 0.426; Copolymer ratio = 73/27.




Figure S2 – An example SEM image of a PDMS coated catheter cross-section. Coating thickness was typically between 5-10 microns. For all images the coating is the light band and PDMS is the grey area.