


Supplementary Materials: The Effect of Elevated Curing Temperatures on High Ye'elite Calcium Sulfoaluminate Cement Mortars

Yeonung Jeong, Craig W. Hargis, Hyunuk Kang, Sung-Chul Chun and Juhyuk Moon

Table 1. Averaged compressive strength and its standard deviation.

| Sample label | Curing Age (days) | Compressive Strength (MPa) | |
|--------------|-------------------|----------------------------|--------------------|
| | | Averaged Value | Standard Deviation |
| CSA1-90 | 1 | 22.20 | 1.94 |
| | 28 | 57.73 | 2.73 |
| CSA2-90 | 1 | 25.93 | 2.82 |
| | 28 | 23.91 | 2.91 |
| CSA1-60 | 1 | 53.20 | 2.04 |
| | 28 | 58.33 | 0.93 |
| CSA2-60 | 1 | 18.61 | 5.69 |
| | 28 | 18.29 | 1.62 |
| CSA1-30 | 1 | 54.72 | 1.22 |
| | 28 | 80.39 | 0.87 |
| CSA2-30 | 1 | 9.78 | 3.18 |
| | 28 | 40.97 | 2.11 |






Figure S1. XQRD results for (a) CSA1-30, (b) CSA2-30, (c) CSA1-60, (d) CSA2-60, (e) CSA1-90, and (f) CSA2-90.



© 2019 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).