

Supplemental Table 1. Different properties of skull bone reported in more recent literature.

	Delille et al. (2007) [5]	Motherway et al. (2009) [6]	Auperrin et al. (2014) [7]	Rahmoun et al. (2014) [8]	Torimitsu et al. (2015) [9]
Testing scenario	Three-point bending	Three-point bending	Three-point bending	Three-point bending	Three-point bending
Velocity	10 mm/min	0.5, 1, 2.5 m/s	10 mm/min	10 mm/min	6 mm/min
Properties					
Elastic modulus (in GPa)	3.6-11.3	4.4-18.1	3.8-9.8	2.0-6.0	<i>Not reported</i>
Bending strength (in MPa)	<i>Not reported</i>	78.2-133.6	<i>Not reported</i>	<i>Not reported</i>	64.3-85.8
Stiffness (in N/mm)	<i>Not reported</i>	<i>Not reported</i>	<i>Not reported</i>	265-640	<i>Not reported</i>