

Table S1 Catalysts for hydrodeoxygenation

Active site	Support	Temperature	Component	Products	Conversion	Ref.
MoO ₃	-	400	Acetone	Propylene	96.8	65[1]
			Cyclohexanone	Pentenes	100	
MoC ₂	-	360	m-cresol	Benzene	90	66[2]
NiMo	Al ₂ O ₃	450	Acetic acid	Ethanol	65	67[3]
Pt	γ -Al ₂ O ₃	300	Guaiacol	phenol	-	72[4]
Pt	HBETA SiO ₂	400	Anisole	benzene	90	73[5]
Pt	Al ₂ O ₃	300	Guaiacol	Anisole	70	74[6]
Pt	γ -Al ₂ O ₃	300	m-cresol	Toluene	74	78[7]
Fe	SiO ₂	400	Guaiacol	Benzene	77	79[8]
Fe	SiO ₂ , AB	400	Guaiacol	Benzene	100	80[9]
Ga	HBETA SiO ₂	400	m-cresol	toluene	80	82[10]
Ru	TiO ₂	400	Pyrolysis vapors			83[11]
W	Carbon	380	propanol/propanal	propene	-	84[12]
Ni	Al ₂ O ₃	260	1-octanol	Octenes	87.4	85[13]
Zn	Al ₂ O ₃	550	Bio-oil		Benzene	86[14]
Cu	Carbon	250-450	Guaiacol	Toluene	65	87[15]
Ni ₂ P	SiO ₂	300	Guaiacol	Phenol	100	93[16]

References:

- [1]. T. Prasomsri, T. Nimmanwudipong, Y. Roman-Leshkov, Effective hydrodeoxygenation of biomass-derived oxygenates into unsaturated hydrocarbons by MoO₃ using low H₂ pressures, *Energy Environ. Sci.* 6 (6) (2013) 1732–1738.
- [2]. Chen, C., W. Lee and A. Bhan, Mo₂C catalyzed vapor phase hydrodeoxygenation of lignin-derived phenolic compound mixtures to aromatics under ambient pressure. *Applied Catalysis A: General*, 2016. 510: p. 42-48.
- [3]. N. Joshi, A. Lawal, Hydrodeoxygenation of acetic acid in a microreactor, *Chem. Eng. Sci.* 84 (2012) 761–771
- [4]. Nimmanwudipong, T., et al., Catalytic Conversion of Guaiacol Catalyzed by Platinum Supported on Alumina: Reaction Network Including Hydrodeoxygenation Reactions. *Energy & Fuels*, 2011. 25(8): p. 3417-3427.
- [5]. Zhu, X., et al., Bifunctional transalkylation and hydrodeoxygenation of anisole over a Pt/HBeta catalyst. *Journal of Catalysis*, 2011. 281(1): p. 21-29.
- [6]. Nimmanwudipong, T., et al., Catalytic Reactions of Guaiacol: Reaction Network and Evidence of Oxygen Removal in Reactions with Hydrogen. *Catalysis Letters*, 2011. 141(6): p. 779-783.
- [7]. Zanuttini, M.S., et al., Deoxygenation of m-cresol on Pt/γ-Al₂O₃ catalysts. *Catalysis Today*, 2013. 213: p. 9-17.
- [8]. Olcese, R.N., et al., Hydrodeoxygenation of Guaiacol, A Surrogate of Lignin Pyrolysis Vapors, Over Iron Based Catalysts: Kinetics and Modeling of the Lignin to Aromatics Integrated Process. *Energy & Fuels*, 2013. 27(2): p. 975-984.
- [9]. Olcese, R., et al., Gas-phase hydrodeoxygenation of guaiacol over iron-based catalysts. Effect of gases composition, iron load and supports (silica and activated carbon). *Applied Catalysis B: Environmental*, 2013. 129: p. 528-538.
- [10]. Ausavasukhi, A., et al., Hydrodeoxygenation of m-cresol over gallium-modified beta zeolite catalysts. *Journal of Catalysis*, 2012. 290: p. 90-100.
- [11]. Wan, S., et al., Direct catalytic upgrading of biomass pyrolysis vapors by a dual function Ru/TiO₂ catalyst. *AIChE Journal*, 2013. 59(7): p. 2275-2285.
- [12]. Ren, H., et al., Tungsten carbides as selective deoxygenation catalysts: experimental and computational studies of converting C₃ oxygenates to propene. *Green Chem*, 2014. 16(2): p. 761-769.
- [13]. Chandra Sekhar Palla, V., D. Shee and S.K. Maity, Kinetics of hydrodeoxygenation of octanol over supported nickel catalysts: a mechanistic study. *RSC Adv.*, 2014. 4(78): p. 41612-41621.
- [14]. S. Karnjanakom, A. Bayu, X. Hao, S. Kongparakul, C. Samart, A. Abudula, G. Guan, Selectively catalytic upgrading of bio-oil to aromatic hydrocarbons over Zn, Ce or Ni-doped mesoporous rod-like alumina catalysts, *J. Mol. Catal. A Chem.* 421(2016) 235–244,
- [15]. J. Sun, A.M. Karim, H. Zhang, L. Kovarik, X.S. Li, A.J. Hensley, J.S. McEwen, Y. Wang, Carbon-supported bimetallic Pd-Fe catalysts for vapor-phase hydrodeoxygenation

of guaiacol, *J. Catal.* 306 (2013) 47–57

[16] P. Bui, J.A. Cecilia, S.T. Oyama, A. Takagaki, A. Infantes-Molina, H. Zhao, D. Li, E. Rodríguez-Castellón, A. Jiménez López, Studies of the synthesis of transition metal phosphides and their activity in the hydrodeoxygenation of a biofuel model compound, *J. Catal.* 294 (2012) 184–198