

LDH-Cellulose Hybrid Beads:

A Novel Catalyst for Topochemical Grafting of Pulp Fibers

LijiSobhana S. Sobhanadhas¹, Lokesh Kesavan², Mika Lastusaari², Pedro Fardim^{1,3*}

¹Laboratory of Fibre and Cellulose Technology, Åbo Akademi University, Porthansgatan 3, FI-20500, Åbo, Finland

²Laboratory of Materials Chemistry and Chemical Analysis, Turku University Centre for Materials and Surfaces (MatSurf), University of Turku, Vatselankatu 2, FI-20014 Turku, Finland

³Department of Chemical Engineering, KU Leuven, Celestijnenlaan 200F bus 2424, B-3001 Leuven, Belgium

Corresponding author email address: pfardim@abo.fi

Powdered LDH catalyst



Separation of the catalyst is difficult



LDH Catalyst supported on Beads



Catalyst

Separation of the catalyst is easier by simple filtration

Fibers

Figure S1: Visualization in understanding the difference between homogeneous and heterogeneous catalysis conditions

Parameters	NiFe LDH	HB
a (Å) (metal-metal distance)	3.08	3.02
c (Å)	23.192	24.78
Basal spacing, (Å)	7.735	8.10

Table S1: Crystallographic parameters of LDH particles and hybrid beads (HB)