

Supplementary Materials

Carvacrol Loaded Solid Lipid Nanoparticles of Propylene Glycol Monopalmitate and Glyceryl Monostearate: Preparation, Characterization, and Synergistic Antimicrobial Activity

Junbo He ^{1,2}, Shuangshuang Huang ¹, Xiaotao Sun ³, Lijuan Han ^{1,2}, Chao Chang ^{1,2}, Weinong Zhang ^{1,2,*} and Qixin Zhong ⁴

¹ Key Laboratory for Deep Processing of Major Grain and Oil, Ministry of Education, College of Food Science & Engineering, Wuhan Polytechnic University, Wuhan 430023, China

² Hubei Key Laboratory for Processing and Transformation of Agricultural Products, Wuhan Polytechnic University, Wuhan 430023, China

³ Beijing Key Lab of Flavor Chemistry, Beijing Technology and Business University, Beijing 100048, China

⁴ Department of Food Science, The University of Tennessee, Knoxville, TN 37996, USA

* Correspondence: zhangweinong@163.com; Tel.: +86-027-8392-4790

Figure S1. ^1H NMR spectra of PGMP. ^1H NMR (400 MHz, DMSO- d_6): 0.85 (t, $J = 4.0$ Hz, 3H), 1.03 (d, $J = 4.0$ Hz, 3H), 1.23 (s, 24H), 1.51 (s, 2H), 2.28 (t, $J = 4.0$ Hz, 2H), 3.78-3.87 (m, 2H).




Figure S2. FT-IR spectra of PGMP. FT-IR (KBr, cm^{-1}): 3404 (stretching of OH), 2919 (stretching of alkyl group), 2849 (stretching of alkyl group), 1743 (stretching of C=O), 1460 (bending vibration of alkyl group), 1248 (skeletal vibration of C-C), 1106 (stretching of C-O), 725 (rocking of long C-H group).




Figure S3. ESI-MS of PGMP. ESI-MS m/z (%): 337.37 ($[\text{M}+\text{Na}]^+$, 100).

