

Table S2: Constitution of the reaction mixtures

Sample name	25 w% PSI solution (mg)	DAB (mg)	CYSE (mg)	DMSO (mg)
CYSE _(1/2)	600.0	6.8	59.5	333.7
CYSE _(1/5)	600.0	6.8	23.8	369.8
CYSE _(1/10)	600.0	6.8	11.9	381.2
CYSE _(1/20)	600.0	6.8	5.9	387.2
CYSE _(1/40)	600.0	6.8	2.9	390.2
CYSE _(1/80)	600.0	6.8	1.5	391.7