

Letter

Highly Reproducible Surface-Enhanced Raman Scattering Detection of Alternariol Using Silver-Embedded Silica Nanoparticles

Eunil Hahm †, Yoon-Hee Kim †, Xuan-Hung Pham and Bong-Hyun Jun *

Department of Bioscience and Biotechnology, Konkuk University, Seoul 05029, Korea; greenice@konkuk.ac.kr (E.H.); yoonhees@konkuk.ac.kr (Y.-H.K.); phamricky@gmail.com (X.-H.P.)

* Correspondence: bjun@konkuk.ac.kr; Tel.: +82-2-450-0521

† E.H. and Y.-H.K. contributed equally to this work.

Received: 28 May 2020; Accepted: 19 June 2020; Published: 22 June 2020

1. Supplementary.




Figure S1. SERS intensity of SiO₂@Ag NPs added to 10⁻⁶ M AOH at 1304 cm⁻¹ after washing with ethanol.




Figure S2. SERS intensity plot at 1254 cm⁻¹ of SiO₂@Ag NPs treated with various concentrations of AOH: (i) 1.000, (ii) 0.500, (iii) 0.250, (iv) 0.125, (v) 0.063, (vi) 0.031, (vii) 0.016, and (viii) 0 μM.




Figure S3. SERS intensity plot at 1609 cm^{-1} of $\text{SiO}_2\text{@Ag}$ NPs treated with various concentrations of AOH: (i) 1.000, (ii) 0.500, (iii) 0.250, (iv) 0.125, (v) 0.063, (vi) 0.031, (vii) 0.016, and (viii) $0\text{ }\mu\text{M}$.




Figure S4. Reproducibility of SERS intensity at 1304 cm^{-1} collected from 10 samples of different NP batches. The samples were prepared by treating each batch of $\text{SiO}_2\text{@Ag}$ NPs with $0.5\text{ }\mu\text{M}$ AOH. The relative standard deviation (RSD) was calculated as 5.65%.