

Supplementary Materials

A comparative study of laser-induced graphene by CO₂ infrared laser and 355 nm Ultraviolet (UV) laser

Liyong WANG ¹, Zhiwen WANG ¹, Ali Naderi Bakhtiyari ¹ and Hongyu ZHENG ^{1,*}

¹ Centre for Advanced Laser Manufacturing (CALM), School of Mechanical Engineering, Shandong University of Technology, Zibo 255000, Shandong

* Correspondence: zhenghongyu@sdut.edu.cn; Tel.: +86-533-2780169

Table S1. The main properties of the PI

Substrate	Type	Thickness	Thermal decomposition temperature	Relative density	Tensile strength
PI	Thermoset	0.125 mm	550°C	1.4	200 MPa




Figure S1. The SEM image of the pristine PI surface

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



© 2020 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).