

Supplementary Materials

Hydrogels Based on Poly(Ether-Ester)s as Highly Controlled 5-Fluorouracil Delivery Systems—Synthesis and Characterization

Adam Kasiński ¹, Monika Zielińska-Pisklak ¹, Ewa Oledzka ¹, Grzegorz Nałęcz-Jawecki ², Agata Drobniewska ², Marcin Sobczak ^{1,*}

- ¹ Department of Biomaterials Chemistry, Chair of Analytical Chemistry and Biomaterials, Faculty of Pharmacy, Medical University of Warsaw, 1 Banacha St., 02-097 Warsaw, Poland; adam.kasinski@wum.edu.pl (A.K.); monikapisklak@o2.pl (M.Z.-P.); ewa.oledzka@wum.edu.pl (E.O.)
- ² Department of Environmental Health Sciences, Faculty of Pharmacy, Medical University of Warsaw, 1 Banacha St., 02-097 Warsaw, Poland; grzegorz.nalecz-jawecki@wum.edu.pl (G.N.-J.); agata.drobniewska@wum.edu.pl (A.D.)
- * Correspondence: marcin.sobczak@wp.pl or marcin.sobczak@wum.edu.pl

Table S1. HPLC gradient for 5-FU analysis.

Time (min)	Phase A (%) (H ₂ O + 0.1 % TFA)	Phase B (%) (ACN + 0.1 % TFA)
0	99	1
7	96	4
12	20	80
15	20	80
20	99	1
25	99	1

Citation: Kasiński, A.; Zielińska-Pisklak, M.; Oledzka, E.; Nałęcz-Jawecki, G.; Drobniewska, A.; Sobczak, M. Hydrogels based on poly(ether-ester)s as highly controlled 5-fluorouracil delivery systems—synthesis and characterization. *Materials* **2020**, *14*, 98. <https://doi.org/10.3390/ma14010098>

Received: 11 November 2020

Accepted: 23 December 2020

Published: 28 December 2020

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2020 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).






Figure S1. The ¹H NMR spectrum of CL-PEG (in CDCl₃).






Figure S4. The ^{13}C NMR spectrum of *rac*-LA-PEG (in CDCl_3).