

Supplementary Information

for

Enhancing clenbuterol immunosensor based on poly(3,4-ethylenedioxythiophene)/multi-walled carbon nanotube performance by response surface methodology

Nurul Ain A. Talib,^{ab} Faridah Salam,^c Nor Azah Yusof,^{ab} Shahrul Ainliah Alang Ahmad,^{ab} Mohd Zulkhairi Azid,^d Razali Mirad^d and Yusran Sulaiman ^{*ab}

^a*Functional Devices Laboratory, Institute of Advance Technology, Universiti Putra Malaysia, 43400 Serdang, Selangor, Malaysia.*

^b*Department of Chemistry, Faculty of Science, Universiti Putra Malaysia, 43400 Serdang, Selangor, Malaysia. E-mail: yusran@upm.edu.my. Tel: +60-389466779. Fax: +60-389435380.*

^c*Biodiagnostic-Biosensor Programme, Biotechnology and Nanotechnology Research Centre, Malaysian Agricultural Research and Development Institute, 43400 Serdang, Selangor, Malaysia.*

^d*Utilization of Agrobiodiversity Resource Programme, Agrobiodiversity and Environmental Research Centre, Malaysian Agricultural Research and Development Institute, 43400 Serdang, Selangor, Malaysia.*

Table of contents

Content	Page no.
Table S1: Central composite design (CCD) for fabrication of PEDOT/MWCNT/Ab-CLB/SPCE using RSM method and results of current response.	2
Table S2: ANOVA table for response surface quadratic model.	3
Fig. S1. 3D surface plots of peak current as a function of (a) pH vs incubation temperature; (b) pH vs Ag incubation time; (c) pH vs blocking; d) incubation temperature vs Ag incubation time; (e) incubation temperature vs blocking; and (f) Ag incubation time vs blocking.	4

Table S1. Central composite design (CCD) for fabrication of PEDOT/MWCNT/Ab-CLB/SPCE using RSM method and results of current response

Standar d	A:		B:	C:	D:	Current (μ A)	
	pH	Incubation temperature (°C)	Ag incubation time (s)	Blocking (%)	Experimental	Predicted	
1	6.4	28	10	0.00	-0.592	-0.577	
2	8.4	28	10	0.00	-0.555	-0.548	
3	6.4	46	10	0.00	-0.494	-0.476	
4	8.4	46	10	0.00	-0.378	-0.400	
5	6.4	28	70	0.00	-0.626	-0.641	
6	8.4	28	70	0.00	-0.687	-0.691	
7	6.4	46	70	0.00	-0.555	-0.569	
8	8.4	46	70	0.00	-0.595	-0.573	
9	6.4	28	10	0.10	-0.620	-0.615	
10	8.4	28	10	0.10	-0.592	-0.602	
11	6.4	46	10	0.10	-0.507	-0.526	
12	8.4	46	10	0.10	-0.510	-0.467	
13	6.4	28	70	0.10	-0.647	-0.649	
14	8.4	28	70	0.10	-0.723	-0.715	
15	6.4	46	70	0.10	-0.608	-0.589	
16	8.4	46	70	0.10	-0.571	-0.609	
17	6.4	37	40	0.05	-0.447	-0.455	
18	8.4	37	40	0.05	-0.444	-0.450	
19	7.4	28	40	0.05	-0.403	-0.408	
20	7.4	46	40	0.05	-0.296	-0.305	
21	7.4	37	10	0.05	-0.473	-0.510	
22	7.4	37	70	0.05	-0.636	-0.613	
23	7.4	37	40	0.00	-0.427	-0.436	
24	7.4	37	40	0.10	-0.468	-0.474	
25	7.4	37	40	0.05	-0.453	-0.416	
26	7.4	37	40	0.05	-0.421	-0.416	

Table S2. ANOVA table for response surface quadratic model

Source	Sum of squares (10^{-3})	Degree of freedom	Mean square (10^{-3})	F-value	Prob > F	Significant
Model	260.74	14	18.62	20.627	< 0.0001	Significant
A	0.09	1	0.09	0.102	0.7556	
B	48.03	1	48.03	53.189	< 0.0001	Significant
C	47.76	1	47.76	52.899	< 0.0001	Significant
D	6.24	1	6.24	6.913	0.0234	Significant
A^2	3.44	1	3.44	3.812	0.0768	
B^2	9.06	1	9.06	10.030	0.0090	Significant
C^2	54.41	1	54.41	60.262	< 0.0001	Significant
D^2	3.89	1	3.89	4.303	0.0623	
AB	2.12	1	2.12	2.347	0.1538	
AC	6.26	1	6.26	6.928	0.0233	Significant
AD	0.27	1	0.27	0.303	0.5932	
BC	0.86	1	0.86	0.947	0.3513	
BD	0.16	1	0.16	0.172	0.6863	
CD	0.92	1	0.92	1.014	0.3355	
Residual	9.93	11	0.90			
Lack of fit	9.42	10	0.94	1.835	0.5227	Not significant
Pure error	0.51	1	0.51			
Corrected total	270.68	25				




Fig. S1. 3D surface plots of peak current as a function of (a) pH vs incubation temperature; (b) pH vs Ag incubation time; (c) pH vs blocking; (d) incubation temperature vs Ag incubation time; (e) incubation temperature vs blocking; and (f) Ag incubation time vs blocking.